Application of nanotechnology in antimicrobial finishing of biomedical textiles

This content has been downloaded from IOPscience. Please scroll down to see the full text.

2014 Mater. Res. Express 1 032003

(<http://iopscience.iop.org/2053-1591/1/3/032003>)

View [the table of contents for this issue](#), or go to the [journal homepage](#) for more

Download details:

IP Address: 193.137.16.114

This content was downloaded on 25/09/2014 at 13:08

Please note that [terms and conditions apply](#).

Topical Review

Application of nanotechnology in antimicrobial finishing of biomedical textiles

Andrea Zille¹, Luís Almeida¹, Teresa Amorim¹, Noémia Carneiro¹,
Maria Fátima Esteves¹, Carla J Silva² and António Pedro Souto¹

¹ 2C2T—Centro de Ciência e Tecnologia Têxtil, Departamento de Engenharia Têxtil, Universidade do Minho, 4800-058 Guimarães, Portugal

² Centro de Nanotecnologia e Materiais Técnicos, Funcionais e Inteligentes (CeNTI), Rua Fernando Mesquita, 2785, 4760-034 Vila Nova de Famalicão, Portugal

E-mail: azille@2c2t.uminho.pt

Received 11 June 2014, revised 8 August 2014

Accepted for publication 27 August 2014

Published 25 September 2014

Materials Research Express 1 (2014) 032003

doi:[10.1088/2053-1591/1/3/032003](https://doi.org/10.1088/2053-1591/1/3/032003)

Abstract

In recent years, the antimicrobial nanofinishing of biomedical textiles has become a very active, high-growth research field, assuming great importance among all available material surface modifications in the textile industry. This review offers the opportunity to update and critically discuss the latest advances and applications in this field. The survey suggests an emerging new paradigm in the production and distribution of nanoparticles for biomedical textile applications based on non-toxic renewable biopolymers such as chitosan, alginate and starch. Moreover, a relationship among metal and metal oxide nanoparticle (NP) size, its concentration on the fabric, and the antimicrobial activity exists, allowing the optimization of antimicrobial functionality.

Keywords: nanoparticles, antimicrobial, textile, zinc, silver, titanium, chitosan

Introduction

In the last 20 years, pathogenic bacteria have developed resistance to almost all the commercially available antibiotics, and the number of new antibiotics expected to enter the market is limited [1]. Thus, searching for new antibacterial agents is a priority for pharmaceutical companies and researchers. Recently, novel antimicrobial agents have been developed using nanoscale materials. Compared to classic antibiotics, these materials have a lower propensity to induce high-level, single-step resistance mutation due to their multi-targeted mechanism of action, high surface area to volume ratio, and unique chemical and physical

properties [2–4]. Numerous types of nanomaterials with antimicrobial properties such as copper [5, 6], zinc [7], titanium [8, 9], magnesium [10], gold [11], chitosan [12] and alginate [13] have been developed in recent years. However, among all, silver nanoparticles (AgNPs) have proved to be the most effective against bacteria, viruses and eukaryotic microorganisms and are being exploited in medicine for burn treatment, dental materials, metal coating, textile fabrics, water treatment and sunscreen lotions [1]. Moreover, silver has proved to have low toxicity to human cells, high thermal stability and low volatility [14]. It is known that the size, shape and crystalline structure of AgNPs affect their toxicological impact on microorganisms. However, the mechanism of bactericidal actions of AgNPs is still not fully elucidated, particularly because most of the available toxicity data are obtained in water or cell culture media, which do not reflect the complex environment inside living organisms [15]. Nowadays, the prevailing paradigm suggests a combination of various factors: (i) Nanoscaled direct interactions between NPs and cell membranes affect their permeability and are followed by a cascade of intracellular reactions, including DNA condensation; (ii) Silver ions reacting with thiol groups of cellular proteins interferes with the bacterial respiratory chain; (iii) Extracellular and intracellular generations of reactive oxygen species have resulted in membrane lipid and DNA damage [14]. Antimicrobial finishing of textiles for biomedical purposes has become an important area of research and one of the fastest growing sectors of the textile market. The global Antimicrobial Coatings Market's worth in 2012 is \$1.5 billion and is estimated to reach \$2.9 billion by 2018, growing at a compound annual growth rate of 11.8% from 2013 to 2018 under normal conditions [16, 17]. In general, the activity of antimicrobial finishes in textiles can be classified as biocidal or biostatic [18]. While the biocides include agents that kill microorganisms, the biostatics inhibit the microorganisms' growth. Antimicrobial textiles commonly use biocides, such as metal nanoparticles (or their salts), quaternary ammonium compounds, poly (hexamethylene biguanide), triclosan and chitosan, as active agents. These agents are either incorporated into the fibers during extrusion or attached to their fiber surface during finishing [19]. However, the definitions of 'bacteriostatic' and 'bactericidal' do not enclose *two* pure categories of antimicrobial agents that exclusively kill bacteria or that only inhibit growth. Within 18–24 h after the test, bactericidal agents usually fail to kill every organism, especially if the inoculum is large, and bacteriostatic agents kill some bacteria [20]. Moreover, the *in vitro* microbiological determination of an antibacterial agent in textiles is also influenced by growth conditions, bacterial density, test duration, extent of reduction in bacterial numbers, fabric shape, morphology and type of material. The most effective methods for testing the efficacy of fabrics that contain antimicrobials are the AATCC 100 and the AATCC 147 from the American Association of Textile Chemists and Colorists. The first test determines both the bacteriostatic activity as well as the bactericidal activity; the second test detects bacteriostatic activity of diffusible antimicrobial agents on treated textile materials by determining a zone of inhibition. However, during the preparation of the manuscript and the compilation of table 1, it became evident that there was a large variety of different tests that could be utilized to determine the fabrics' antimicrobial activity as well as a lack of information about the methodologies utilized to determine whether an antibacterial agent is bactericidal or bacteriostatic. Most antibacterial textiles are better described as potentially being both bactericidal and bacteriostatic, but in this review, they have been considered 'bactericidal' textiles only when able to kill more than 99.9% of the inoculum.

Currently, nanotechnology is considered the most promising technology for novel textile commercial applications since it allows the permanent and effective functionalization of

Table 1. Antimicrobial nanomaterials applied on textiles.

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
Acrylic					
[Ag]	1–7	Photocured Carboxymethyl Starch NPs	20* [<i>S. aureus</i>] 15* [<i>E. coli</i>]	1* [<i>S. aureus</i>] (15) 0.5* [<i>E. coli</i>] (15)	[127]
Bamboo					
[Ag]	<100	NPs grafted with acrylic acid	98.7 [<i>S. aureus</i>] 100 [<i>E. coli</i>]	84.9 [<i>S. aureus</i>] (50) 96.2 [<i>E. coli</i>] (50)	[128]
[CuO]	<100 [1 wt.%]	NPs grafted with acrylamide	100 [<i>S. aureus</i>] 99 [<i>E. coli</i>]	75 [<i>S. aureus</i>] (50) 75 [<i>E. coli</i>] (50)	[94]
[ZnO]	10 [14 $\mu\text{g g}^{-1}$]	NPs grafted with HSDA	99.1 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	99 [<i>S. aureus</i>] (20) 98.9 [<i>E. coli</i>] (20)	[87]
Cellulose acetate					
[Ag]	3–16 [0.05 wt.%]	Electrospun nanofibers containing NPs	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>] 99.9 [<i>K. pneumoniae</i>] 99.9 [<i>P. aeruginosa</i>]	n.a.	[104]
	21 [0.5 wt.%]	Electrospun nanofibers containing NPs	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>] 99.9 [<i>K. pneumoniae</i>] 99.9 [<i>P. aeruginosa</i>]	n.a.	[129]
Cotton					
[Alginate/TSA]	99 [70 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	99 [<i>E. coli</i>] (30)	[130]
[Ag]	0.65 [7 wt.%]	Colloid NPs padded on fabric	1.21* [<i>S. aureus</i>]	0 [<i>S. aureus</i>] (5)	[23]
	1–2 [0.8 wt.%]	Silica–silver core–shell particle deposited by Pad-dry-cure method	<1* [<i>E. coli</i>]	n.a.	[40]
	1.6 [10 $\mu\text{g g}^{-1}$]	Biosynthesized NPs impregnated on cotton	99 [<i>S. aureus</i>]	n.a.	[131]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
	2–5 [3.17 wt.%]	Colloid NPs synthesized and adsorbed on fabric	99.9 [<i>S. typhimurium</i>] 97 [<i>S. aureus</i>]	96 [<i>S. typhimurium</i>] (30) 93 [<i>S. aureus</i>] (30)	[98]
	2–12 [1215 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion method	6–7* [<i>E. coli</i>]	n.a.	[39]
	2–12 [385 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion method	4–5* [<i>E. coli</i>]	n.a.	[39]
	2–5 [30 $\mu\text{g g}^{-1}$]	Colloid NPs padded on fabric	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	94.5 [<i>K. pneumoniae</i>] (20) 97.2 [<i>S. aureus</i>] (20)	[132]
	2–6	NPs–poly(acrylate) clusters impregnated on fabric	>1* [<i>S. aureus</i>] >1* [<i>S. epidermidis</i>] >1* [<i>P. aeruginosa</i>] >1* [<i>C. albicans</i>]	n.a.	[44]
	2–8 [0.7 wt.%]	Cellulose–Gum polymer–Ag nanocomposite adsorbed by exhaustion method	>1.7* [<i>E. coli</i>]	n.a.	[49]
	3 [20 $\mu\text{g g}^{-1}$]	Colloid NPs padded on fabric	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	99.9 (10)	[25]
	3–20 [336 $\mu\text{g g}^{-1}$]	Colloid NPs/PEG adsorbed by exhaustion method	10.5* [<i>E. coli</i>] 6.7* [<i>S. aureus</i>]	1* [<i>E. coli</i>] (50) 1.8* [<i>S. aureus</i>] (50)	[133]
	3–20 [336 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion method	2–3* [<i>E. coli</i>]	n.a.	[39]
	3–20 [894 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion method	5–6* [<i>E. coli</i>]	n.a.	[39]
	3–8 [108 $\mu\text{g g}^{-1}$]	Biosynthesized NPs padded on fabric	96 [<i>E. coli</i>] 98 [<i>S. aureus</i>]	55 [<i>E. coli</i>] (20) 59 [<i>S. aureus</i>] (20)	[24]
	5	Dodecanethiol-capped NPs in silica sol	40 [<i>E. coli</i>]	n.a.	[42]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
	6–8 [$100 \mu\text{g g}^{-1}$]	Pad-dry-cure method	96 [<i>E. coli</i>] 98.3 [<i>S. aureus</i>]	59 [<i>E. coli</i>] (20) 62 [<i>S. aureus</i>] (20)	[48]
	6–8 [$50 \mu\text{g g}^{-1}$]	Pad-dry-cure method	96 [<i>E. coli</i>] 96.4 [<i>S. aureus</i>]	56.6 [<i>E. coli</i>] (20) 60.9 [<i>S. aureus</i>] (20)	[48]
	7–11 [$758 \mu\text{g g}^{-1}$]	Microwave synthesized colloid NPs padded on fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	37 [<i>E. coli</i>] (15) 26 [<i>S. aureus</i>] (15)	[134]
	8	Pad-dry-cure method	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	99.9 [<i>E. coli</i>] (30) 99.9 [<i>S. aureus</i>] (20)	[135]
	10	NPs with dendrimers in Pad-dry-cure method	95 [<i>E. coli</i>] 95 [<i>S. aureus</i>]	n.a.	[50]
	10 [$50 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>] 99.9 [<i>C. albicans</i>]	99.9 (5)	[136]
	10–20	Colloid NPs impregnated by US	63.6 [<i>B. linens</i>] 62.7 [<i>S. epidermidis</i>]	n.a.	[137]
	10–110 [$8.2 \mu\text{g g}^{-1}$]	Spherical AgNPs deposition by US	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	0 [<i>S. aureus</i>] (5) 0 [<i>E. coli</i>] (5)	[34]
	11	NPs grafted with HBP-NH ₂	99.4 [<i>S. aureus</i>] 99.4 [<i>E. coli</i>]	96.7 [<i>S. aureus</i>] (50) 96.5 [<i>E. coli</i>] (50)	[138]
	15–30	NPs adsorbed by exhaustion method	20 [<i>F. oxysporum</i>] 25 [<i>A. brassicicola</i>]	n.a.	[139]
	18 [$88 \mu\text{g g}^{-1}$]	Colloid NPs with HBP-NH ₂ impregnated on fabric	99 [<i>E. coli</i>] 99.3 [<i>S. aureus</i>]	98.8 [<i>E. coli</i>] (20) 99 [<i>S. aureus</i>] (20)	[45]
	20	Covalent bond of AgNPs polystyrene-block-polyacrylic acid reverse micelle cores	>20* [<i>E. coli</i>] >1* [<i>S. aureus</i>]	0* [<i>E. coli</i>] (5) >1* [<i>S. aureus</i>] (20)	[140]
	20 [2 wt.%]		>1.5* [<i>E. coli</i>]	n.a.	[141]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
		Colloid NPs impregnated on fabric			
	20–110 [14.1 $\mu\text{g g}^{-1}$]	Disc AgNPs deposition by US	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	0 [<i>S. aureus</i>] (5) 0 [<i>E. coli</i>] (5)	[34]
	20–60 [1500 $\mu\text{g g}^{-1}$]	UV-assisted Pad-dry-cure method	>1* [<i>E. coli</i>] >1.5* [<i>S. aureus</i>]	<1* [<i>E. coli</i>] (10) >1.5* [<i>S. aureus</i>] (10)	[58]
	30 [54 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion in CF ₄ -plasma treated fabric	77 [<i>P. aeruginosa</i>] 68 [<i>E. faecalis</i>]	n.a.	[60]
	30–50	Colloid NPs adsorbed by exhaustion method	99.9 [<i>E. coli</i>] 99.8 [<i>S. epidermis</i>]	93.3 [<i>E. coli</i>] (20) 90.8 [<i>S. epidermis</i>] (20)	[142]
	30–200 [140 $\mu\text{g g}^{-1}$]	Silica/AgNPs Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	32–64 [12.8 $\mu\text{g g}^{-1}$]	Prism AgNPs deposition by US	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	12.5 [<i>S. aureus</i>] (5) 49.9 [<i>E. coli</i>] (5)	[34]
	35–80 [0.5 wt.%]	Colloid NPs deposition by UV	5* [<i>E. coli</i>] 4* [<i>S. aureus</i>] 5* [<i>C. albicans</i>] 3* [<i>P. p43</i>]	n.a.	[143]
	41 [5300 $\mu\text{g g}^{-1}$]	Ethanol solution of AgNO ₃ and butylamine impregnated on fabric	98 [<i>E. coli</i>] 95 [<i>S. aureus</i>]	n.a.	[43]
	50 [30 wt.%]	Gas-phase reaction between phosphine and copper sulphate and AgNO ₃	100 [<i>S. aureus</i>]	100 [<i>S. aureus</i>] (10)	[144]
	50 [9.4 $\mu\text{g g}^{-1}$]	Polygonal AgNPs deposition by US	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	25 [<i>S. aureus</i>] (5) 0 [<i>E. coli</i>] (5)	[34]
	60 [100 $\mu\text{g g}^{-1}$]	NPs and BTCA impregnated on fabric	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	96 [<i>E. coli</i>] 92 [<i>S. aureus</i>] (30)	[46]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[Ag/Chitosan]	75	Microfibers containing NPs by UV irradiation	80 [<i>E. coli</i>]	n.a.	[57]
	80 [26 $\mu\text{g g}^{-1}$]	Colloid NPs adsorbed by exhaustion in CF ₄ -plasma treated fabric	<60 [<i>P. aeruginosa</i>] <60 [<i>E. faecalis</i>]	n.a.	[60]
	80 [6 wt.%]	Synthesis and deposition of NPs using US irradiation	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	n.a.	[54]
	180 [4 wt.%]	Colloid NPs padded on fabric	1.66* [<i>S. aureus</i>]	4.2* (5)	[23]
	200 [350 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	99 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>P. aeruginosa</i>]	n.a.	[145]
	200 [452 $\mu\text{g g}^{-1}$]	Colloid NPs padded on fabric	99.9 [<i>E. coli</i>] 99.8 [<i>S. aureus</i>]	n.a.	[146]
	>200 [16.8 $\mu\text{g g}^{-1}$]	Hierarchical AgNPs deposition by US	99.9 [<i>S. aureus</i>] 99.9 [<i>E. coli</i>]	91.3 [<i>S. aureus</i>] (5) 99.9 [<i>E. coli</i>] (5)	[34]
	257 [34.5 wt.%]	NPs impregnated on fabric	99.9 [<i>E. coli</i>]	199.9 [<i>E. coli</i>] (10)	[147]
	40 [1 wt.%]	Pad-dry-cure method	31* [<i>E. coli</i>] 26* [<i>S. aureus</i>]	15* [<i>E. coli</i>] (20) 17* [<i>S. aureus</i>] (20)	[148]
	50–175	Colloid NPs impregnated on fabric	3* [<i>E. coli</i>]	n.a.	[52]
[Ag/Chitosan/TiO ₂] [Chitosan]	5000 [7 wt.%]	Pad-dry-cure method	98 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	n.a.	[149]
	5–180 [0.5 wt.%]	Colloid NPs impregnated on fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	65 [<i>E. coli</i>] (20) 78 [<i>S. aureus</i>] (20)	[124]
	40	Colloid NPs impregnated on fabric by US	5 [<i>E. coli</i>] 25 [<i>E. faecalis</i>]	n.a.	[123]
[Chitosan/Alginate]	350 [0.8 wt.%]	NPs grafted with GPTMS	80 [<i>E. coli</i>] 80 [<i>M. luteus</i>]	n.a.	[125]
	35			95 [<i>B. cereus</i>] (30) 87 [<i>E. coli</i>] (30) 98 [<i>P.</i>	[150]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[CuO]		Pad-dry-cure method of NPs loaded with leaf extract	100 [<i>B. cereus</i>] 98 [<i>E. coli</i>] 100 [<i>P. aeruginosa</i>] 100 [<i>S. aureus</i>]	<i>aeruginosa</i>] (30) 98 [<i>S. aureus</i>] (30)	
	10 [5 wt.%]	Colloid NPs impregnated on fabric by US	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[56]
	10–20 [1.5 wt.%]	Colloid NPs impregnated on fabric by US	99.8 [<i>E. coli</i>]	n.a.	[55]
	15 [1.4 wt.%]	Colloid NPs impregnated on fabric by US	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[91]
	40–60 [0.2 wt.%]	Pad-dry-cure method	93.7 [<i>E. coli</i>] 95 [<i>S. aureus</i>]	48 [<i>E. coli</i>] (15) 45 [<i>S. aureus</i>] (15)	[151]
	50	Microencapsulated NPs adsorbed by exhaustion method	92.71 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	86 [<i>E. coli</i>] (10) 92 [<i>S. aureus</i>] (10)	[38]
	60–75 [2 wt.%]	Pad-dry-cure method	86.5 [<i>E. coli</i>] 94.2 [<i>S. aureus</i>]	9.8 [<i>E. coli</i>] (20) 12 [<i>S. aureus</i>] (20)	[92]
	60–80 [0.7 wt.%]	Colloid NPs impregnated on fabric by US	73 [<i>E. coli</i>] 66 [<i>S. aureus</i>] 72 [<i>MRSA</i>] 50 [<i>A. baumannii</i>] 74 [<i>P. aeruginosa</i>]	5 [<i>E. coli</i>] (65) 46 [<i>S. aureus</i>] (65)	[95]
	100–150	Colloid NPs coated by pad-dry-cure method	80 [<i>E. coli</i>] 99 [<i>S. aureus</i>] 98 [<i>A.niger</i>]	n.a.	[93]
200–400 [0.74 wt.%]	Colloid NPs impregnated on fabric by US	38 [<i>E. coli</i>] 38 [<i>S. aureus</i>] 52 [<i>K. pneumonia</i>] 52 [<i>MRSA</i>] 1 [<i>A. baumannii</i>] 15 [<i>P. aeruginosa</i>]	n.a.	[152]	
[TiO ₂]	7 [2 wt.%]	Pad-dry-cure method	72.9 [<i>S. aureus</i>] 74.5 [<i>K. pneumonia</i>]	29.9 [<i>S. aureus</i>] (20) 30.5 [<i>K. pneumonia</i>] (20)	[153]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[ZnO]	10–15 [6 wt.%]	Colloid anatase NPs impregnated on fabric by US	25 [<i>E. coli</i>] 94.4 [<i>S. aureus</i>] 59.5 [<i>C. albicans</i>]	n.a.	[154]
	10–15 [8 wt.%]	Colloid rutile NPs impregnated on fabric by US	6.9 [<i>E. coli</i>] 72.4 [<i>S. aureus</i>] 40.3 [<i>C. albicans</i>]	n.a.	[154]
	10–15 [6 wt.%]	Colloid anatase NPs impregnated on fabric by US + UV	29.2 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>] 70.1 [<i>C. albicans</i>]	n.a.	[154]
	10–15 [8 wt.%]	Colloid rutile NPs impregnated on fabric by US + UV	31.9 [<i>E. coli</i>] 99.3 [<i>S. aureus</i>] 62.4 [<i>C. albicans</i>]	n.a.	[154]
	12m [2 wt.%]	Pad-dry-cure method	75.8 [<i>S. aureus</i>] 77.6 [<i>K. pneumonia</i>]	34.7 [<i>S. aureus</i>] (20) 34.7 [<i>K. pneumonia</i>] (20)	[153]
	13–20 [1 $\mu\text{g g}^{-1}$]	Pad-dry-cure method	94 [<i>E. coli</i>] 99 [<i>S. aureus</i>]	83 [<i>E. coli</i>] (10) 86 [<i>S. aureus</i>] (10)	[76]
	<50 [5 wt.%]	Colloid NPs impregnated on fabric	98 [<i>S. aureus</i>] 98 [<i>K. pneumoniae</i>]	n.a.	[75]
	70–390 [0.5 wt.%]	Apatite-coated NPs by pad-dry-cure method	5.5 [<i>E. coli</i>] 13.4 [<i>S. aureus</i>] 24.2 [<i>M. luteus</i>]	n.a.	[74]
	10–20 [0.8 wt.%]	Colloid NPs impregnated on fabric by US	17 [<i>E. coli</i>]	n.a.	[55]
	20–100	Colloid NPs impregnated on fabric by US	100 [<i>S. aureus</i>]	n.a.	[155]
	25	ZnO nanoparticle incorporated PS-b-PAA coating	>1* [<i>S. aureus</i>] >1* [<i>E. coli</i>]	n.a.	[156]
	30–40 [0.66 wt.%]	Roll to roll US coating on enzyme pre-treated fabric	36 [<i>S. aureus</i>] 35 [<i>P. aeruginosa</i>] 25 [<i>A.</i>	15 [<i>S. aureus</i>] (10) 30 [<i>P. aeruginosa</i>] (10) 12 [<i>A. baumannii</i>] (10) 30	[157]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[ZnO/Chitosan]			<i>baumannii</i>] 70 [<i>E. coli</i>] 31 [MRSA]	[<i>E. coli</i>] (10) 32 [MRSA] (10)	
	30–60 [10 wt.%]	Pad-dry-cure method	99 [<i>E. coli</i>] 98 [<i>M. luteus</i>]	n.a.	[158]
	30 [0.75 wt.%]	Colloid NPs deposition by US	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[83]
	37 [20 wt.%]	Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	n.a.	[159]
	38 [0.2 wt.%]	Pad-dry-cure method	91.8 [<i>S. aureus</i>] 15 [<i>K. pneumoniae</i>]	n.a.	[84]
	38 [0.6 wt.%]	Pad-dry-cure method	96.8 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	n.a.	[84]
	38 [1 wt.%]	Pad-dry-cure method	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	n.a.	[84]
	<50	Colloid NPs impregnated on fabric	97 [<i>S. aureus</i>] 98 [<i>K. pneumoniae</i>]	n.a.	[75]
	60–70 [0.75 wt.%]	Roll to roll US coating on fabric	36 [<i>S. aureus</i>] 18 [<i>P. aeruginosa</i>] 11 [<i>A. baumannii</i>] 65 [<i>E. coli</i>] 38 [MRSA]	15 [<i>S. aureus</i>] (10) 12 [<i>P. aeruginosa</i>] (10) 0 [<i>A. baumannii</i>] (10) 5 [<i>E. coli</i>] (10) 10 [MRSA] (10)	[157]
	<100	Layer-by-layer deposition of NPs	1.3* [<i>S. aureus</i>]	0 [<i>S. aureus</i>] (20)	[85]
	80–150 [4.3 wt.%]	Nanorods and chalcone solution padded on fabric	99.9 [<i>E. coli</i>] 99.6 [<i>S. aureus</i>] 99.9 [<i>P. aeruginosa</i>]	n.a.	[36]
	200 [2 wt.%]	Pad-dry-cure method	80 [<i>E. coli</i>] 99.6 [<i>S. aureus</i>]	75 [<i>E. coli</i>] (5) 98 [<i>S. aureus</i>] (5)	[160]
	15–60 [0.3 wt.%]	Colloid NPs impregnated on fabric by US	99.9 [<i>E. coli</i>] 98.5 [<i>S. aureus</i>]	85 [<i>E. coli</i>] (10) 70 [<i>S. aureus</i>] (10)	[161]
	28–100 [6 wt.%]	Pad-dry-cure method		n.a.	[89]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[ZrO]	30	Pad-dry-cure method	22* [<i>E. coli</i>] 25* [<i>S. aureus</i>]	n.a.	[162]
			100 [<i>E. coli</i>] 100 [<i>M. luteus</i>]		
	60 [0.5 wt.%]	Colloid NPs impregnated on fabric by US	40 [<i>E. coli</i>] 48 [<i>E. faecalis</i>]	n.a.	[123]
	2–5 [2.41 wt.%]	Colloid NPs synthesized and adsorbed on fabric	98 [<i>S. typhimurium</i>] 95 [<i>S. aureus</i>]	92 [<i>S. typhimurium</i>] (30) 90 [<i>S. aureus</i>] (30)	[98]
Cotton/polyester					
[Ag]	30–200 [59 $\mu\text{g g}^{-1}$]	Silica/AgNPs Pad-dry-cure method (65/35)	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	100 [1000 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric (60/40)	100 [<i>S. aureus</i>]	100 [<i>S. aureus</i>] (4)	[163]
[TiO₂]	<50 [5 wt.%]	Colloid NPs impregnated on fabric (55/45)	98 [<i>S. aureus</i>] 99 [<i>K. pneumoniae</i>]	n.a.	[75]
[ZnO]	30	Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>M. luteus</i>]	n.a.	[162]
	30–60 [10 wt.%]	Pad-dry-cure method (65/35)	98 [<i>E. coli</i>] 99 [<i>M. luteus</i>]	n.a.	[158]
	<50	Colloid NPs impregnated on fabric (55/45)	98 [<i>S. aureus</i>] 99 [<i>K. pneumoniae</i>]	n.a.	[75]
Polyacrylonitrile					
[Chitosan]	1000 [15 wt.%]	Electrospun nanofibers containing Chitosan	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 99.8 [<i>P. aeruginosa</i>] 100 [<i>M. luteus</i>]	n.a.	[122]
Polyamide					
[Ag]	8	Electrospun nanofibers containing NPs	99.9 [<i>E. coli</i>]	n.a.	[105]
	10 [4.46 $\mu\text{g g}^{-1}$]		99.9 [<i>C. albicans</i>]	64.7 [<i>C. albicans</i>] (5)	[70]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
		Colloid NPs impregnated on corona-plasma treated fabric			
	10 [4.46 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	83.2 [<i>E. coli</i>] (5) 85.3 [<i>S. aureus</i>] (5)	[63]
	10 [4.46 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated dyed fabric	98.6 [<i>C. albicans</i>]	n.a.	[64]
	10 [4.46 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated dyed fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[164]
	10–20 [0.025 wt.%]	Thermal reduction of silver acetate during melt processing of PA	80.6 [<i>E. coli</i>]	n.a.	[101]
	10–20 [0.06 wt.%]	Thermal reduction of silver acetate during melt processing of PA	99.9 [<i>E. coli</i>]	n.a.	[101]
	30–200 [31 $\mu\text{g g}^{-1}$]	Silica/AgNPs Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	50–100 [1 wt.%]	Colloid NPs impregnated on fabric by US	99 [<i>P. aeruginosa</i>] 99 [<i>S. aureus</i>]	n.a.	[66]
	70	Colloid NPs impregnated on fabric	5–6* [<i>E. coli</i>]	n.a.	[165]
	80	Colloid NPs impregnated on dyed fabric	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>P. aeruginosa</i>]	0 [<i>E. coli</i>] 0 [<i>S. aureus</i>] 0 [<i>P. aeruginosa</i>]	[166]
	<100	Layer-by-layer deposition of NPs	53 [<i>S. aureus</i>]	n.a.	[167]
[CuO]	85 [8.5 wt.%]		>1* [<i>S. aureus</i>]	n.a.	[97]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
		In situ produced NPs grafted with CTAB			
[TiO ₂]	21 [1 wt.%]	Electrospun nanofibers containing NPs	99 [<i>E. coli</i>]	n.a.	[73]
[ZnO]	<100 [5 wt.%]	Sheath-core fibers prepared by melt-spinning method	100 [<i>S. aureus</i>] 100 [<i>K. pneumoniae</i>]	n.a.	[86]
	<100 [1 wt.%]	Sheath-core fibers prepared by melt-spinning method	95 [<i>S. aureus</i>] 68 [<i>K. pneumoniae</i>]	n.a.	[86]
Poly(ϵ-caprolactone)					
[Ag-Zr(HPO ₄) ₂]	63.7 [1 wt.%]	Electrospun nanofibers containing NPs	98.4 [<i>E. coli</i>] 99.3 [<i>S. aureus</i>]	n.a.	[106]
Polyester					
[Ag]	2–5	Colloid NPs padded on fabric	99.7 [<i>S. aureus</i>] 99.8 [<i>K. pneumoniae</i>]	15.3 [<i>K. pneumoniae</i>] (20) 84.3 [<i>S. aureus</i>] (20)	[132]
	2–6	Silver–poly(acrylate) NPs clusters impregnated on fabric	>1* [<i>S. aureus</i>] >1* [<i>S. epidermidis</i>] >1* [<i>P. aeruginosa</i>] >1* [<i>C. albicans</i>]	n.a.	[44]
	3 [10 $\mu\text{g g}^{-1}$]	Colloid NPs padded on fabric	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	n.a.	[25]
	10	NPs with dendrimers in Pad-dry-cure method	95 [<i>E. coli</i>] 60 [<i>S. aureus</i>]	n.a.	[50]
	10 [8.61 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated fabric	99.1 [<i>C. albicans</i>]	96.7 [<i>C. albicans</i>] (5)	[70]
	10 [8.61 $\mu\text{g g}^{-1}$]				[63]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
		Colloid NPs impregnated on corona-plasma treated fabric	99.9 [<i>E. coli</i>] 99.8 [<i>S. aureus</i>]	99.9 [<i>E. coli</i>] (5) 99.6 [<i>S. aureus</i>] (5)	
	10 [$8.61 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated dyed fabric	99.9 [<i>C. albicans</i>]	n.a.	[64]
	10 [$8.61 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated dyed fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[164]
	11 [1 wt.%]	NPs plasma grafted with acrylic acid	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	n.a.	[168]
	<20 [$10 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	100 [<i>S. aureus</i>] 42 [<i>K. pneumoniae</i>]	n.a.	[169]
	<20 [$100 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	100 [<i>S. aureus</i>] 100 [<i>K. pneumoniae</i>]	n.a.	[169]
	30–200 [$8.9 \mu\text{g g}^{-1}$]	Silica/AgNPs Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	40–70 [$155 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on RF-plasma treated fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	99.9 [<i>E. coli</i>] (5) 99.9 [<i>S. aureus</i>] (5)	[61]
	80 [$93 \mu\text{g g}^{-1}$]	Colloid NPs impregnated on corona-plasma treated fabric	19 [<i>E. coli</i>] 67 [<i>S. aureus</i>] 74 [<i>S. faecalis</i>] 6 [<i>P. aeruginosa</i>]	n.a.	[62]
[Ag/Chitosan]	166 [0.2 wt.%]	Colloid NPs impregnated on PVP treated fabric	100 [<i>S. aureus</i>]	n.a.	[53]
[Chitosan]	5–180 [0.5 wt.%]	Colloid NPs impregnated on fabric	90 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	50 [<i>E. coli</i>] (20) 75 [<i>S. aureus</i>] (20)	[124]
	115 [0.2 wt.%]	Colloid NPs impregnated on PVP treated fabric	90 [<i>S. aureus</i>]	n.a.	[53]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[Fe ₃ O ₄]	30–40	In situ synthesis of NPs	100 [<i>S. aureus</i>]	n.a.	[100]
[α -Fe ₂ O ₃]	40–50	In situ synthesis of NPs	80.5 [<i>S. aureus</i>]	n.a.	[100]
[SiO ₂ /Ag/CuO]	500/30/17 [2.5 wt.%]	Top-coating with Pericoat PU 340 NEW paste containing NPs	100 [<i>E. coli</i>] 99.8 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>] 100 [<i>C. albicans</i>] 99.4 [<i>A. niger</i>] 96.5 [<i>T. mentagraphytes</i>]	99.9 [<i>E. coli</i>] (20) 99.8 [<i>S. aureus</i>] (20) 99.9 [<i>K. pneumoniae</i>] (20) 100 [<i>C. albicans</i>] (20) 56.4 [<i>A. niger</i>] (20) 92.1 [<i>T. mentagraphytes</i>] (20)	[170]
[TiO ₂]	6 [2.1 wt.%]	Alginate and colloid NPs impregnated on fabric	99.9 [<i>E. coli</i>]	99.8 (5)	[171]
Polyethylene [Ag/Chitosan]	5 [1.1 wt.%]	Electrospun nanofibers containing NPs	99.9 [<i>E. coli</i>]	n.a.	[107]
Polyethylene/Chitosan [Ag]	12–18 [1.3 wt.%]	Electrospun nanofibers containing NPs	15* [<i>E. coli</i>] 20* [<i>S. aureus</i>] 18* [<i>P. aeruginosa</i>] 12* [<i>C. albicans</i>]	n.a.	[172]
Polyethylene/polypropylene [Ag]	<10 [12 μ g g ⁻¹]	Colloid NPs padded on non-woven fabric	99.8 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	n.a.	[173]
Poly(l-lactide) [Ag]	30 [32 wt.%]	Electrospun nanofibers containing NPs	94.2 [<i>E. coli</i>] 98.5 [<i>S. aureus</i>]	n.a.	[108]
	35 [5 wt.%]	Electrospun nanofibers containing NPs	5* [<i>E. coli</i>] 5* [<i>S. aureus</i>]	n.a.	[109]
Polypropylene [Ag]	15 [0.3 wt.%]			n.a.	[103]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
		Sheath-core fibers prepared by melt-spinning method	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]		
	30 [0.1 wt.%]	Twin-screw mixer extrusion	99.9 [<i>S. aureus</i>]	n.a.	[102]
[TiO ₂ /Ag]	60–100 [0.2 wt.%]	Sheath-core fibers prepared by melt-spinning method	99.2 [<i>S. aureus</i>]	n.a.	[78]
Poly(vinyl alcohol)					
[Ag]	6 [0.1 wt.%]	Electrospun nanofibers containing NPs	99.9 [<i>S. aureus</i>] 99.9 [<i>K. pneumoniae</i>]	n.a.	[110]
[Ag/Chitosan]	2–10 [1 wt.%]	Electrospun nanofibers containing NPs	99.9 [<i>E. coli</i>]	n.a.	[111]
	20 [0.6 wt.%]	Electrospun PVA nanofibers containing NPs	100 [<i>E. coli</i>]	n.a.	[51]
[TiO ₂ /Ag/Chitosan]	100 [0.04 wt.%]	Electrospun nanofibers containing NPs	99 [<i>E. coli</i>] 98 [<i>S. aureus</i>]	n.a.	[79]
Poly(vinyl alcohol)/Silk					
[Ag]	3.8	Electrospun nanofibers containing NPs	>1* [<i>E. coli</i>] >1* [<i>S. aureus</i>]	n.a.	[112]
Silk					
[Ag]	4.3 [116.5 µg g ⁻¹]	Colloid NPs and PNP impregnated on fabric	99.5 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	98.9 [<i>E. coli</i>] (30) 99.4 [<i>S. aureus</i>] (30)	[174]
	5–50 [2.3 wt.%]	Colloid NPs impregnated on fabric	99.9 [<i>S. aureus</i>]	n.a.	[175]
	15–30	Colloid NPs adsorbed by exhaustion method	45 [<i>F. oxysporum</i>] 50 [<i>A. brassicola</i>]	n.a.	[139]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
	10 [40 $\mu\text{g g}^{-1}$]	Colloid NPs applied by exhaustion	100 [<i>S. aureus</i>]	84 [<i>S. aureus</i>] (10)	[176]
	<10	UV-assisted in situ synthesis of AgNPs	1.59* [<i>E. coli</i>] 1.84* [<i>S. aureus</i>]	n.a.	[65]
	<10 [50 $\mu\text{g g}^{-1}$]	Colloid NPs applied by exhaustion in US bath	94 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	n.a.	[177]
	11.5 [13 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	>1* [<i>M. lysodeikticus</i>] >1* [<i>E. coli</i>] >1* [<i>S. aureus</i>]	n.a.	[178]
	<20	Synthesis of NPs on silk fibers via γ -ray irradiation	96 [<i>S. aureus</i>]	85 [<i>S. aureus</i>] (10)	[179]
	30–200 [170 $\mu\text{g g}^{-1}$]	Silica/AgNPs Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	35 [60 $\mu\text{g g}^{-1}$]	Colloid NPs applied by exhaustion	100 [<i>S. aureus</i>]	78 [<i>S. aureus</i>] (10)	[176]
	50 [268.6 $\mu\text{g g}^{-1}$]	Colloid NPs impregnated on fabric	99 [<i>E. coli</i>]	98 [<i>E. coli</i>] (50)	[180]
	<100 [98.7 $\mu\text{g g}^{-1}$]	Multi-amidine/silver nitrate sol added by steam method	99.9 [<i>E. coli</i>] 99.5 [<i>S. aureus</i>]	>97.4 [<i>E. coli</i>] (50)	[181]
	<100	Colloid NPs impregnated on fabric	100 [<i>E. coli</i>]	n.a.	[182]
	<100	Layer-by-layer deposition of NPs	80 [<i>S. aureus</i>]	n.a.	[167]
[Au]	21 [0.21 wt.%]	<i>In situ</i> synthesized NPs impregnated on fabric	100 [<i>E. coli</i>]	n.a.	[99]
[Chitosan]	20.8 [1 wt.%]	Colloid NPs impregnated on fabric	95 [<i>S. aureus</i>]	90 [<i>S. aureus</i>] (20)	[183]
[TiO ₂]	50 [25 $\mu\text{g g}^{-1}$]			n.a.	[184]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[TiO₂/Ag] Viscose [Ag] [Chitosan] Wool [Ag]	20/5 [1 wt.%]	Colloid NPs and PUA applied by dyeing DHPBA modified NPs padded on fabric	19* [<i>E. coli</i>] 23* [<i>S. aureus</i>] >1* [<i>E. coli</i>] >1* [<i>S. aureus</i>] >1* [<i>P. aeruginosa</i>]	n.a.	[80]
	2–9 [4 wt.%]	AgNPs SiO ₂ Sol-gel coating	53 [<i>A. niger</i>] 41 [<i>B. subtilis</i>] 88 [<i>P. putida</i>]	n.a.	[185]
	30–200 [230 µg g ⁻¹]	Silica/AgNPs Pad-dry-cure method	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 100 [<i>A. niger</i>]	n.a.	[41]
	5–180 [0.5 wt.%]	Colloid NPs impregnated on fabric	99.9 [<i>E. coli</i>] 99.9 [<i>S. aureus</i>]	55 [<i>E. coli</i>] (20) 76 [<i>S. aureus</i>] (20)	[124]
	1–7	Photocured Carboxymethyl Starch NPs	24* [<i>S. aureus</i>] 22* [<i>E. coli</i>]	3* [<i>S. aureus</i>] (15) 1* [<i>E. coli</i>] (15)	[127]
	2–6	Silver–poly(acrylate) NPs clusters impregnated on fabric	>1* [<i>C. albicans</i>]	n.a.	[44]
	4.2 [5 µg g ⁻¹]	Colloid silver NPs impregnated by pad-dry-cure	99.9 [<i>S. aureus</i>] 99.7 [<i>K. pneumoniae</i>]	n.a.	[186]
	15 × 6	Nanodisc colloid NPs impregnated on fabric	98.5 [<i>E. coli</i>]	n.a.	[35]
	22 × 14	Nanodisc colloid NPs impregnated on fabric	93.8 [<i>E. coli</i>]	n.a.	[35]
	45–60	Colloid NPs adsorbed by exhaustion method	99.9 [<i>E. coli</i>] 98.9 [<i>S. epidermis</i>]	92 [<i>E. coli</i>] (20) 91.7 [<i>S. epidermis</i>] (20)	[142]
	48 × 5	Nanoprism colloid NPs impregnated on fabric	77 [<i>E. coli</i>]	n.a.	[35]
				n.a.	[41]

Table 1. (Continued.)

Textile fabric and fiber [Nanomaterial]	NPs average size (nm) [Concentration]	Method	% Bacterial reduction [Strain]	% Bacterial reduction after washing [Strain] (Washing cycles)	Reference
[SiO ₂ /Ag]	30–200 [310 µg g ⁻¹]	Silica/AgNPs Pad-dry-cure method	18 [<i>E. coli</i>] 56 [<i>S. aureus</i>] 50 [<i>A.niger</i>]		
	34.6	Colloid NPs impregnated on fabric	71 [<i>E. coli</i>]	n.a.	[187]
	60 [4.3 wt.%]	Colloid NPs impregnated on RF-plasma treated fabric	85 [<i>E. coli</i>] 95 [<i>S. aureus</i>]	70 [<i>E. coli</i>] (20) 73 [<i>S. aureus</i>] (20)	[71]
[TiO ₂ /Ag]	21 [1 wt.%]	TiO ₂ NPs in silver nitrate solution impregnated on fabric	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>]	n.a.	[81]
Wool/polyester					
[Ag]	30–200 [250 µg g ⁻¹]	Silica/AgNPs Pad-dry-cure method (45/55)	100 [<i>E. coli</i>] 100 [<i>S. aureus</i>] 0 [<i>A.niger</i>]	n.a.	[41]
[TiO ₂]	21 [0.25 wt.%]	Colloid NPs crosslinked with BTCA on fabric (45/55)	99 [<i>E. coli</i>]	n.a.	[188]
	21 [0.75 wt.%]	Colloid NPs crosslinked with BTCA on fabric (45/55)	100 [<i>E. coli</i>]	n.a.	[188]

*Inhibition zone in mm; n.a. Not available.

substrates without affecting their macro-scale properties, such as breathability or hand feel [18]. Nanoparticles as antimicrobial agents have increasingly been used in textile research due to their unique physico-chemical properties and biological activity, which may differ significantly from ion and bulk materials [21]. However, nanoparticles (NPs) in humans may affect normal cellular proliferation and protein functions primarily due to their metallic nature, and the generation of reactive oxygen species may initiate pro-inflammatory and toxic activities [22]. The first chapter of the manuscript is dedicated to AgNPs because most of the research in this field was conducted using this metal. For the same reason, because the majority of the information regarding the effect of NP morphology and deposition methods was only studied on silver, three subchapters (NP morphology, chemical deposition methods and physical deposition methods) were added. The first subchapter is dedicated to the importance of size, shape, composition, crystallinity and structure of NPs on their antimicrobial activity. The second is dedicated to chemical deposition methods, with special emphasis on the new routes for the deposition of NPs based on environmental benign natural polymers. The third subchapter is about physical deposition methods, focusing on plasma technology. The following chapters report on research using other antimicrobial metal and metal oxide NPs and nanofibers. The last chapter reports on the recent use of natural polymer NPs, especially chitosan, in the antimicrobial finishing of textiles due to the environmental and toxicological concerns regarding the use of heavy metals for the production of NPs. Thus, due to the increasing dichotomy between environmental and health concerns and the potential benefits of using NPs as finishing agents, this review offer the opportunity to update and critically discuss the latest advances and applications for the textile industry.

Nanosilver

As we can see in table 1, several methods have been used for surface nanomodifications of textiles, but most of the research has been performed using nanosilver immobilized on cotton, polyester, polyamide, silk and wool fabrics by conventional dip- or pad-dry methods [23–25]. The term ‘nanosilver’ is conventionally attributed to silver metals, but a fraction of the silver salts could also fall under the NP definition according to the International Standard Organisation (ISO), which defines an NP as having a maximum diameter of 100 nm in at least three dimensions. However, all particles with a diameter between 100 to 1000 nm were also assumed to contain NPs, unless there was concrete information about the size distribution and the stability of agglomerates. Taking this into account, according to Windler *et al* up to 80% of all silver used in textiles (45 metric tonnes) may be considered in the nanoform [26]. Considerable work has been done in the functionalization of textile materials with AgNPs. Most of the research is focused on the antimicrobial effects of modified textile materials, but no evident conclusions about the binding mechanism between AgNPs and textile fibers has been proposed. Thus, due to the huge amount of AgNP-containing textiles, some concerns have been raised about the release of silver into the environment after repeated washing [27, 28]. Some authors questioning the use of AgNPs of lower than 30 nm in textiles due to the additional effort it requires towards synthesis, stabilization and incorporation when the same results could be obtained simply by immersing the fabric in solutions of AgNO₃ [29]. The critics are basing their questions on the difficulties in achieving small particle sizes of narrow size distributions with green processes and on the toxicity concerns of particles with a size between 1 and 10 nm,

Figure 1. Close-up of the TEM image of AgNPs (X200000 magnification) in different shapes and sizes. (1) Cubic, (2) Spherical ~10 nm, (3) Triangular, (4) Spherical ~60 nm, (5) Rod-like. TEM was performed using a JEOL JEM 1400 TEM (Tokyo, Japan) operating at an acceleration voltage of 120 kV. Nanoparticle sample was applied to glow-discharged carbon-coated copper grids followed by negative staining with a solution of 1% (w/v) uranyl acetate.

which can penetrate human skin [30]. Nowadays, the release of silver is an emerging environmental problem. Therefore, it is expected that further research will be more oriented towards the environmental, nanotechnological and regulatory aspects of the exploitation of textile products with deposited or immobilized NPs [31].

NP morphology

The way in which NPs alter surface properties and impart textile antimicrobial functions is mainly determined by their size, shape, composition, crystallinity and structure [32]. It has been described that AgNPs of between 1 and 10 nm present a greater impact on bacteria than larger particles, and that triangular-shaped NPs display greater biocidal action than rod- or spherical-shaped ones [33]. Recent results of studies on the antimicrobial effect on cotton fabric of different morphologies of AgNPs, such as spherical, polygonal, disk, prism, and hierarchical assemblies (figure 1), confirmed that non-spherical morphologies, such as polygonal-, prism- and hierarchical-like shapes, in comparison with spherical and disc morphologies exhibited a stronger growth-inhibitory effect against Gram-negative and Gram-positive bacteria. In addition, among various tested morphologies, the hierarchical-like morphology showed very good antimicrobial activity after five washing cycles [34]. On the other hand, in a few other works available in the literature using nano-rods, -discs and -prisms in textiles, moderate biocide activity is shown when compared with conventional spherical-shaped NPs [35, 36]. Supposedly, the significantly larger surface area of the NPs allows higher contact with bacteria, enhancing their bactericidal activity. However, other factors, such as dielectric and quantum confinement effects, could be responsible for the different properties of metal or metal-oxide NPs with respect to bulk materials [37].

Chemical deposition methods

Most of the methods used in AgNP production are based on reactions in the liquid medium and often require environmentally hazardous surfactants, reducing agents and templates for the synthesis of AgNPs [38, 39]. Several studies reporting on silica–silver core–shell NPs mainly review the chemical synthesis processes and their characterization. Silica is a class of very important core materials for immobilizing NPs on its surface due to its high chemical and thermal stability, chemical inertness, large surface areas, and good compatibility with other materials. Nischala *et al* synthesized extremely small (1–2 nm) AgNPs attached on silica core particles with an average size of 270 nm using a simple one-pot chemical method. The silver containing silica core–shell particles immobilized on cotton did not leach out from the fabric and showed excellent antibacterial activity even after 10 washing cycles [40]. Novel fiber–silica–Ag composites with biocidal activity were also successfully produced by chemically modifying cotton, wool, silk, polyester and polyamide fabrics. The results show that the chemical and morphological structures of the fibers directly influenced their absorptivity and affinity for the AgNPs. On the other hand, a chemical strong-binding of Ag to the fibers seems to significantly reduce the effectiveness of the antimicrobial activity of the AgNPs [41]. Other methods include the reduction of silver ions by ethanol or isopropanol or the coating with acrylates or cross-linkable polysiloxanes to stabilize NP dispersion onto the fabric [32, 42–46]. The introduction of green chemistry into nanotechnology is one of the most important topics in nanoscience research today. The main purpose is to avoid the environmental toxicity or biological hazards normally associated with the preparation of AgNPs using synthetic reducing agents. To date, new routes for the development of NPs based on environmentally benign natural polymers such as chitosan, hyaluronan, starch, and cyclodextrin have been explored [47]. Hebeish *et al* synthesized small AgNPs using hydroxypropyl starch as both a reducing and stabilizing agent, retaining excellent antibacterial properties even after 20 washing cycles, reflecting the importance of binders in the fixation of AgNPs on the surface of the fabrics [48]. Raghavendra *et al* tested on cellulose fibers several natural carbohydrates such as gum acacia and gaur gum as an effective reducing agent for the green synthesis of AgNPs from AgNO₃. The thermal stability and mechanical properties of the cellulosic composites were found to be better than cellulose fibers alone [49]. Mahltig *et al* fabricated hybrid nanomaterials based on dendrimers as polymeric stabilizers for the preparation of AgNPs used as finishing agents to produce antimicrobial textiles. The results confirmed that the antimicrobial effect rises with increases in the dendrimers' generations due to decreasing size of the formed AgNPs. By changing thermal fixation and dendrimers' generations, the strength of the antimicrobial effect can be controlled [50]. Several works involve chemical modification of textile fabrics by natural, biocompatible and biodegradable polysaccharide chitosan followed by incorporating AgNPs into the fabrics. Abdelgawad *et al* produced antibacterial nanofiber mats of PVA loaded with AgNPs enveloped in chitosan after reduction with glucose. The results showed superior properties and synergistic antibacterial effects by combining chitosan with AgNPs [51]. Other authors produced silver-loaded chitosan NPs attached to textiles, which also exhibited excellent antibacterial activity [52, 53].

Figure 2. SEM images (X4000 magnification) of antimicrobial AgNP aggregates deposited on DBD plasma pre-treated polyamide 6,6 fibers. Images were carried in a FEG-SEM, NOVA 200 Nano SEM, FEI Company. Secondary and backscattering electron images were performed with an acceleration voltage of 5 kV and 15 kV, respectively. Samples were covered with a film of Au–Pd (80–20 wt.%) in a high-resolution sputter coater, 208 h Cressington Company, coupled to a MTM-20 Cressington High Resolution Thickness Controller.

Physical deposition methods

In the last decade, physical methods such as ultrasound [54–56], UV irradiation [57–59], plasma pre-treatment and ion-beam-assisted deposition [60–64] have been proved to be effective for the deposition, insertion and synthesis of well-dispersed nanophase materials on textiles. Lu *et al* developed a UV-assisted *in situ* synthesis approach to immobilize AgNPs on silk fibers for antibacterial applications. Results show that AgNPs with excellent crystalline structures are efficiently attached on the silk surface in an irradiation time-dependent manner [65]. Sonochemical reactions are capable of enhancing AgNP adhesion to the fabric surface by physical or chemical bonding depending on the nature of the substrate [66]. Pre-treatment of textiles by low-pressure plasmas can also improve loading of AgNPs from colloids (figure 2). Different plasma particles (e.g. electrons, ions, free radicals, photons) provide superficial functionalization and etching of the fiber without deterioration of bulk properties. Plasma is particularly important for the surface activation of hydrophobic synthetic fibers such as polyester and polyamide fabrics because it makes fibers more accessible to water and chemical species [67–69]. However, little research using plasma pre-treatment reports about antimicrobial activity on fabrics. The Serbian group headed by M Radetic reported great stability and uniform AgNPs coatings, as well as high antibacterial activity and laundering durability, using several plasma sources such as low-temperature air radio frequency (RF), dielectric barrier discharge (DBD) and corona discharge in different textile materials [61, 63, 64, 70]. Although RF-powered plasma devices allow easier control of properties and uniformity, this system requires more complex handling and a vacuum system, which can be avoided by using DBD and corona discharges at atmospheric pressure. Other groups working with plasma (including corona and

CF₄-plasma) have obtained similar results on AgNPs deposition, but with lower biocide performance [60, 62, 71].

Nanotitanium dioxide

Nano TiO₂, one of the most powerful photocatalytic materials, possesses high activity, strong oxidizing power and long-term stability [72]. When illuminated under UV light with wavelengths lower than 385 nm, nano TiO₂ electrons are excited from the valence band to the conduction band [73]. The positive hole in the valence band can then react with water or hydroxide ions adsorbed on the surface to produce hydroxyl radicals, and the electron in the conduction band can reduce O₂ to produce superoxide ions. These two highly reactive species are able to decompose a variety of organic materials, including microorganisms [74]. However, there are few reports on the use of TiO₂ nanomaterial for textile applications, and only NPs with a diameter lower than 20 nm have shown effective, but not complete, antimicrobial activity in cotton, polyester, polyamide and wool/polyester fabrics [73–75].

Khurana *et al* observed that cationic as well as non-ionic dispersing agents led to a reduction in size of the TiO₂ NPs produced by sol gel methods, whereas anionic dispersing agents led to an increase in particle size. The TiO₂ NPs so synthesized were successfully applied onto cotton while maintaining their antimicrobial activity for up to 10 washes with the help of a binder [76]. Although there are numerous advantages in utilizing nano TiO₂ in textiles, some drawbacks have also been reported. First, due to its high band gap, semiconductor TiO₂ shows photocatalytic activity under UV rays, which practically limits the use of sunlight or visible light as an irradiation source. Second, the electron-hole recombination rate is too high, resulting in low photocatalytic efficiency. It has been suggested that through adding noble metals to the surface of TiO₂, photocatalytic activity can be increased by extending the light absorption range of TiO₂ from UV to the visible range [77]. Some examples using mixed silver/TiO₂ are found in the existing literature for polypropylene, poly (vinyl alcohol), silk and wool, but they did not apparently show any additional advantages over silver [78–81]. Moreover, the dissipation mechanism of the UV energy is not often considered. A direct application of TiO₂ to products such as paint, textile, plastics and paper can lead to the creation of free radicals with consequent photochemical decomposition of the substrates [74]. Free radicals are also implicated in a number of potential health issues such as skin aging. However, free radical generation can be reduced by over 90% by incorporating a dopant ion within the titanium oxide lattice structure [82].

Nanozinc oxide

ZnO NPs exhibit strong antibacterial activities on a broad spectrum of bacteria on cotton [36, 55, 75, 83–85], polyamide [86] and bamboo fabric [87]. Moreover, excellent multi-functional textiles with good UV protection in addition to very good antibacterial properties against Gram positive and Gram negative bacteria can be obtained using ZnO in combination with synthetic [88] and natural organic polymers such as chitosan [89]. The use of functional polymer matrices such as PMME or PNIPAM as a dispersion medium for ZnO NPs results in improved functional and bonding properties in fabrics (figure 3). Similar to TiO₂, the photocatalytic generation of hydrogen peroxide was suggested to be one of the primary

Figure 3. SEM images (X1500 and X50000 magnification) of antimicrobial ZnO NPs—PNIPAM composite coated on DBD plasma pre-treated cotton fibers. Images were carried in a FEG-SEM, NOVA 200 Nano SEM, FEI Company. Secondary and backscattering electron images were performed with an acceleration voltage of 5 kV and 15 kV, respectively. Samples were covered with a film of Au–Pd (80–20 wt.%) in a high-resolution sputter coater, 208 h Cressington Company, coupled to a MTM-20 Cressington High Resolution Thickness Controller.

mechanisms. In addition, penetration of the cell envelope and disorganization of bacterial membrane upon contact with ZnO NPs were also indicated to inhibit bacterial growth. However, the role of the Zn^{2+} ion released from the dissolution of ZnO is not yet clear, and the antibacterial mechanism of ZnO is still under investigation [90].

Nanocopper

Limited information, almost exclusively on cotton, is available on the antimicrobial activity and action mechanism of nano CuO in textiles [38, 55, 56, 91–93]. CuO is cheaper than silver, easily mixed with polymers and relatively stable in terms of both chemical and physical properties. Very recently, Teli *et al* have developed a bamboo rayon fabric grafted with acrylamide utilized to immobilize copper NPs. The product showed antibacterial activity against Gram-positive and Gram-negative bacteria and was found to be durable until 50 washes [94]. Perelshtein *et al* has recently sonochemically coated a cotton fabric with CuO NPs while maintaining antibacterial properties even after 65 cycles of washings according to hospital protocols of hygienic washing (75 °C) [95]. However, in comparison with AgNPs, higher concentrations of CuO are required to achieve a comparable bactericidal effect [96]. Moreover, CuO NPs synthesis is often more challenging in comparison to noble metals such as silver and gold. Copper sulphate in aqueous solution tends to form Cu_2O due to the relatively low $\text{CuO}/\text{Cu}^{2+}$ redox potential and spontaneous oxidation of the NPs in ambient conditions. This last drawback can be avoided by protecting copper NPs against oxidation during preparation and storage using non-aqueous solvents, surfactants or ligands to prevent NP agglomeration during the process of synthesis [97].

Other metals and metal oxides

Very few examples are found in the existing literature about the use of other nanomaterials in textiles for antibacterial purposes. Gouda *et al* has used *in situ* synthesized zirconium oxide NPs deposited into cotton gauze fabrics. ZrO₂ NPs gave a 98% and 95% reduction rate in colony count against Gram-positive and Gram-negative bacteria, respectively. However, antifungal activity was lower than that of fabrics treated with nanosilver. No skin irritation was observed, and all prepared samples were durable enough to wash even after 30 laundering washing cycles [98]. Tang *et al* developed a simple *in situ* synthesis route for gold NPs to be applied to multi-functionalized silk fabrics. The AuNPs were prepared in a heated solution containing white silk fabric samples. Silk fabrics treated with AuNPs showed strong antibacterial activity, excellent UV protection properties and enhanced thermal conductivity. However, silk fabrics were colored red and brown by the AuNPs because of their localized surface plasmon resonance property [99]. Harifi *et al* prepared multi-functional polyester fabric with magnetic, antibacterial and sono-Fenton catalytic activities by *in situ* synthesis of magnetite and hematite NPs using ferric chloride, ferrous sulphate and sodium hydroxide. The results suggest the potential of the proposed method in producing fabrics with durable magnetic properties that are suitable for various applications such as electromagnetic shielding, antibacterial fabrics and sono-Fenton catalyst for dye discoloration [100]. In their review, Dastjerdi and Montazer discussed other nano-structured, antimicrobial agents with a potential for textile modification, including carbon nanotubes, nanoclay and its modified forms, and gallium- and liposome-loaded NPs; however, no textile applications have yet been developed [32].

Nano-additivated fibers and nanofibers

Several methods also include the bulk modification of conventional filament yarns of polyamide or polypropylene with various concentrations of different nanocomposite fillers, such as Ag, chitosan, PVA, ZnO, TiO₂ and mixed Ag/TiO₂, via melt mixing [86, 101, 102]. Yeo and Jeong, for example, produced bi-component, sheath-core fibers prepared by using a melt-spinning method with polypropylene chips and AgNPs. However, the fibers containing AgNPs in the core part showed no antibacterial activity. Only fibers having AgNPs in the sheath part showed antibacterial activity [103]. On the other hand, Dastjerdi *et al* produced biostatic polypropylene filament yarns with various blending contents of nanocomposite based on Ag/TiO₂ NPs using a twin-screw extruder. However, despite having good biostatic properties, none of the tested blends displayed a bactericide effect [78]. The bulk modification of filament yarns with various concentrations of nanocomposite fillers via melt mixing is an environmentally friendly and easily adjustable modification method. However, it is limited to synthetic fibers, and the particles situated in the central part of the filaments hardly contribute to the fibers' antibacterial properties. Although the production of core-shell bi-component fibers can be helpful in removing this disadvantage, the required systems are not easily adaptable to industrial standards. A similar problem is also noticeable in the case of reduction of metallic salts to NPs in the bulk polymeric matrix [32].

These problems, however, could be solved by the use of electrospun nanofibers due to their high surface-area-to-volume and length-to-diameter ratios (figure 4) [73, 79, 104–112]. Electrospinning is a process carried out at room temperature that allows the production of

Figure 4. SEM images (X50000 magnification) of antimicrobial nanofibers obtained from PVA and chitosan (left), and PVA and AgNO_3 (right). Images were carried in a FEG-SEM, NOVA 200 Nano SEM, FEI Company. Secondary and backscattering electron images were performed with an acceleration voltage of 5 kV and 15 kV, respectively. Samples were covered with a film of Au–Pd (80–20 wt.%) in a high-resolution sputter coater, 208 h Cressington Company, coupled to a MTM-20 Cressington High Resolution Thickness Controller.

polymer fibers with diameters in the sub-micron size range, through the application of an external electric field, keeping intact the bulk properties of the polymers. Because of unique properties such as a high surface-to-volume ratio, very good mechanical performance, high porosity and diameters in the nanoscale, electrospun mats made from ultrafine polymer fibers have been drawing great attention for antimicrobial coatings. Moreover, electrospinning is a high quality, environmentally friendly and easily adjustable method for industrial applications. Several researchers have investigated the spinnability of different polymers. For instance, electrospun nanofibers of cellulose acetate, PVA, PAN and polyester urethane were used to disperse several antimicrobial materials, such as spherical gold and AgNPs, Fe_2O_3 , gallium nitride, zirconium carbide and carbon nanotubes [113–115]. Suspension of AgNPs directly combined into electrospinning polymer solutions is the most used method to prepare composite nanofibers. However, nanofibers produced using this method have demonstrated diminished antimicrobial efficiency due to nanoparticle aggregation. A more efficient method was the *in situ* reduction of silver ions in pre-electrospinning solutions, resulting in a more uniform dispersion of AgNPs [116].

Electrospun nanofibers based on chitosan and chitosan NPs applied on several textiles such as cotton, viscose and polyester fabrics have also been extensively investigated. Solutions of pure chitosan are not electrospinnable, independently of their polysaccharide concentrations, mainly due to the high surface tension and conductivities of chitosan acetic acid solutions. Electrospun antimicrobial nanofibers may, however, be fabricated from blended systems of chitosan and fiber-forming polymers such as nylon, cellulose acetate, PEO, PET, PAN and PVA [117–119]. Electrospinning allows extensive tunability in material properties and functions through the selection of polymeric nanofibers, ceramic nanofibers, metallic nanofibers or composite nanofibers. Ideally, nanofibers should be made into continuous yarn before weaving into textile fabrics. However, the diameter of the yarn collected using this process was less than $5\text{ }\mu\text{m}$ and it is uncertain whether the yarn was strong enough to be woven into textiles since

several studies showed that insufficient nanofibers in the bundle would result in yarn breakage [120]. For these reasons, now the majority of the electrospun nanofibers incorporating antimicrobial properties are utilized for the production of filtration membranes in order to reduce the formation of biofilm, which is a common source of membrane fouling.

Chitosan

Due to the environmental and toxicological concerns about the use of heavy metals for the production of NPs, researchers have been recently exploring the use of natural polymers, especially chitosan, in the antimicrobial finishing of textiles. Chitosan $[(C_6H_{11}O_4N)_n]$, the N-deacetylated derivative of chitin $[(C_8H_{13}O_5N)_n]$ due to the presence of amino groups, is a cationic polyelectrolyte, one of the few occurring in nature. This gives chitosan singular chemical and biological characteristics, such as biocompatibility, antibacterial properties, heavy metal ion chelation ability, gel-forming properties and hydrophilicity. The use of chitosan NPs in protein and drug delivery systems is being actively researched and reported in the literature [121]. However, the research on chitosan NPs for textile applications is limited because most of the literature is based on the use of bulk chitosan as a coating or finishing agent. Antimicrobial fabrics with nanocoated chitosan have proved to be a durable, cost-effective and eco-friendly process. Some research has shown, however, that chitosan NPs have a less inhibiting effect on *S. aureus* compared to bulk chitosan since NPs have less positive charge available to bind to the negative bacterial cell wall. Conversely, other researchers reported that chitosan NPs exhibit higher antibacterial activity due to the NP's larger surface area and higher affinity with bacteria cells, which yield a quantum-size effect [53, 122–125]. These contradictory results suggest that the antimicrobial mode of action of chitosan is not a simple mechanism, but is an intricate event-driven process that needs further investigation [126].

Conclusions

Most of the literature about antimicrobial textile nanocomposites is focused on silver. However, other metals and metal oxides such as zinc, titanium, copper, zirconium, iron and gold show improved biocidal properties at nanoscale. ZnO and CuO nanocomposites display similar performance compared to silver while TiO₂ efficacy is limited by light availability due to its photocatalytic mechanism of action. Despite the heterogeneous range of methods, textile substrates, nanoparticle sizes and concentrations that can be found in the literature, some general assumptions can be made about metal and metal oxide NPs based on the collected data. Silver and copper NPs of between 1 and 15 nm showed the best biocide activity at relatively low concentrations on the fabrics (5–50 ppm or 1–2 wt.%). AgNPs of up to 50 nm, still require relatively low concentrations of around 100 ppm or 5 wt.% to have complete Gram-positive and Gram-negative inhibition effects. Titanium oxide NPs applied to textiles are generally in the size range of 1–20 nm. With some exceptions, TiO₂ NPs showed low antimicrobial activity (an average of 70%) even at high concentrations of 10 wt.% on the fabrics. This occurs mainly because TiO₂ NPs are fully effective just under UV rays, which limits their practical use in the textile industry. On the other hand, ZnO NPs need a higher average size of 30–40 nm, but with a lower concentration (around 1 wt.%) than TiO₂ to be effective. This is possibly due to the synergetic dual effect of the photocatalytic generation of hydrogen peroxide and the direct

disorganization of the bacterial membrane. However, despite the promising results, the available information of ZnO NPs on textiles is still limited. All types of metal and metal oxide NPs with diameters greater than 100 nm need concentrations comparable to the metal ions or bulk materials to achieve the same antimicrobial performance.

The bacterial species *Staphylococcus aureus* (Gram positive), *Escherichia coli* (Gram negative) and *Klebsiella pneumoniae* (Gram negative) are the most-tested strains. Some authors have also tested different bacteria and fungi such as *Candida albicans*. However, the eukaryotic cytotoxicity and allergic reactions in humans are not considered in NP-containing textiles. Moreover, few authors have tested the antimicrobial efficiency after a reasonable number (at least 20) of washing cycles, limiting the precise estimation of the amount and form of NPs released from the fabrics into the environment. The risk assessment of the nanomaterials used in commercial textile products requires a better understanding of nanomaterial mobility, bioavailability and toxicity in the environment. Due to this increasing dichotomy between environmental and health concerns and the potential benefits of using NPs as an antimicrobial finish for textiles, the use of natural polymers, especially chitosan, and electrospun nanofibers have been recently explored. The research about chitosan NPs deposited on fabrics is still at an early stage; however, from the little information available, it is possible to estimate that the average sizes range from 20–200 nm and that the effective concentration is usually lower than 1 wt.%. The latest research in this field seems to indicate an emerging new paradigm in the production and distribution of NPs for textile applications utilizing non-toxic renewable biopolymers such as chitosan, alginate and starch.

Acknowledgement

Andrea Zille (C2011-UMINHO-2C2T-01) acknowledges funding from Programa Compro-misso para a Ciência 2008, Portugal.

Author contributions

Andrea Zille performed the AgNP synthesis, AgNP deposition on polyamide fabrics, SEM and TEM analysis of the AgNPs and nanofibers, analyzed the data, interpreted results, elaborated table 1 and wrote the review. Noémia Carneiro performed the ZnO NPs synthesis, ZnO NPs deposition on cotton fabrics, SEM analysis of the deposited ZnO NPs, analyzed data, interpreted results, help in the table elaboration and reviewed the manuscript. António Pedro Souto performed the DBD plasma pre-treatment of the fabrics, analyzed data, interpreted results, helped with the table elaboration and reviewed the manuscript. Carla J Silva has prepared the electrospun nanofibers. Luís Almeida, Teresa Amorim and Maria Fátima Esteves analyzed data, interpreted results, helped with the table elaboration and reviewed The manuscript.

References

- [1] Rai M, Yadav A and Gade A 2009 Silver nanoparticles as a new generation of antimicrobials *Biotechnol. Adv.* **27** 76–83

- [2] Allahverdiyev A M, Abamor E S, Bagirova M and Rafailovich M 2011 Antimicrobial effects of TiO₂ and Ag₂O nanoparticles against drug-resistant bacteria and leishmania parasites *Future Microbiol.* **6** 933–40
- [3] Geoprincy G, Saravanan P, Gandhi N N and Renganathan S 2011 A novel approach for studying the combined antimicrobial effects of silver nanoparticles and antibiotics through agar over layer method and disk diffusion method *Dig. J. Nanomater. Biostruct.* **6** 1557–65
- [4] Jia Q M, Shan S Y, Jiang L H, Wang Y M and Li D 2012 Synergistic antimicrobial effects of polyaniline combined with silver nanoparticles *J. Appl. Polym. Sci.* **125** 3560–6
- [5] Ramyadevi J, Jeyasubramanian K, Marikani A, Rajakumar G and Rahuman A A 2012 Synthesis and antimicrobial activity of copper nanoparticles *Mater. Lett.* **71** 114–6
- [6] Ren G G, Hu D W, Cheng E W C, Vargas-Reus M A, Reip P and Allaker R P 2009 Characterisation of copper oxide nanoparticles for antimicrobial applications *Int. J. Antimicrob. Agents* **33** 587–90
- [7] Stanic V, Dimitrijevic S, Antic-Stankovic J, Mitric M, Jokic B, Plecas I B and Raicevic S 2010 Synthesis, characterization and antimicrobial activity of copper and zinc-doped hydroxyapatite nanopowders *Appl. Surf. Sci.* **256** 6083–9
- [8] Schabes-Retchkiman P S, Canizal G, Herrera-Becerra R, Zorrilla C, Liu H B and Ascencio J A 2006 Biosynthesis and characterization of Ti/Ni bimetallic nanoparticles *Opt. Mater.* **29** 95–9
- [9] Martinez-Gutierrez F, Olive P L, Banuelos A, Orrantia E, Nino N, Sanchez E M, Ruiz F, Bach H and Av-Gay Y 2010 Synthesis, characterization, and evaluation of antimicrobial and cytotoxic effect of silver and titanium nanoparticles *Nanomed.-Nanotechnol. Biol. Med.* **6** 681–8
- [10] Lellouche J, Kahana E, Elias S, Gedanken A and Banin E 2009 Antibiofilm activity of nanosized magnesium fluoride *Biomaterials* **30** 5969–78
- [11] Perni S, Piccirillo C, Pratten J, Prokopovich P, Chrzanowski W, Parkin I P and Wilson M 2009 The antimicrobial properties of light-activated polymers containing methylene blue and gold nanoparticles *Biomaterials* **30** 89–93
- [12] Qi L F, Xu Z R, Jiang X, Hu C H and Zou X F 2004 Preparation and antibacterial activity of chitosan nanoparticles *Carbohydr. Res.* **339** 2693–700
- [13] Singh R and Lillard J W Jr 2009 Nanoparticle-based targeted drug delivery *Exp. Mol. Pathol.* **86** 215–23
- [14] Marambio-Jones C and Hoek E M V 2010 A review of the antibacterial effects of silver nanomaterials and potential implications for human health and the environment *J. Nanopart. Res.* **12** 1531–51
- [15] Pal S, Tak Y K and Song J M 2007 Does the antibacterial activity of silver nanoparticles depend on the shape of the nanoparticle? A study of the gram-negative bacterium *Escherichia coli* *Appl. Environ. Microbiol.* **73** 1712–20
- [16] Gao Y and Kyratzis I L 2012 Antimicrobial finishing of wool using an oxidative pretreatment to enhance the exhaustion of quaternary ammonium compounds *J. Appl. Polym. Sci.* **125** E71–8
- [17] VV A A 2013 Antimicrobial coatings market by type (silver, copper, & others), application (indoor air/HVAC, medical, mold remediation, building & construction, food & beverages, textiles, & others) & geography (North America, Europe, Asia-Pacific, and ROW)—global trends and forecasts to 2018 *Top Market Reports* (Dallas, TX, US) (marketsandmarkets.com)
- [18] Sundarajan S, Chandrasekaran A R and Ramakrishna S 2010 An update on nanomaterials-based textiles for protection and decontamination *J. Am. Ceram. Soc.* **93** 3955–75
- [19] Simoncic B and Tomsic B 2010 Structures of novel antimicrobial agents for textiles—a review *Text. Res. J.* **80** 1721–37
- [20] Pankey G A and Sabath L D 2004 Clinical relevance of bacteriostatic versus bactericidal mechanisms of action in the treatment of gram-positive bacterial infections *Clin. Infect. Dis.* **38** 864–70
- [21] Gao Y and Cranston R 2008 Recent advances in antimicrobial treatments of textiles *Text. Res. J.* **78** 60–72
- [22] Moritz M and Geszke-Moritz M 2013 The newest achievements in synthesis, immobilization and practical applications of antibacterial nanoparticles *Chem. Eng. J.* **228** 596–613
- [23] Ghosh S, Yadav S and Reynolds N 2010 Antibacterial properties of cotton fabric treated with silver nanoparticles *J. Text. Inst.* **101** 917–24

- [24] El-Rafie M H, Mohamed A A, Shaheen T I and Hebeish A 2010 Antimicrobial effect of silver nanoparticles produced by fungal process on cotton fabrics *Carbohydr. Polym.* **80** 779–82
- [25] Lee H J 2005 Bacteriostasis and skin innocuousness of nanosize silver colloids on textile fabrics *Text. Res. J.* **75** 551–6
- [26] Windler L, Height M and Nowack B 2013 Comparative evaluation of antimicrobials for textile applications *Environ. Int.* **53** 62–73
- [27] Chernousova S and Eppele M 2013 Silver as antibacterial agent: ion, nanoparticle, and metal *Angew. Chem. Int. Ed.* **52** 1636–53
- [28] Geranio L, Heuberger M and Nowack B 2009 The behavior of silver nanotextiles during washing *Environ. Sci. Technol.* **43** 8113–8
- [29] Emam H E, Manian A P, Široká B, Duelli H, Redl B, Pipal A and Bechtold T 2013 Treatments to impart antimicrobial activity to clothing and household cellulosic-textiles—why ‘nano’-silver? *J. Cleaner Prod.* **39** 17–23
- [30] Auffan M, Rose J, Bottero J Y, Lowry G V, Jolivet J P and Wiesner M R 2009 Towards a definition of inorganic nanoparticles from an environmental, health and safety perspective *Nat. Nanotechnol.* **4** 634–41
- [31] Radetić M 2012 Functionalization of textile materials with silver nanoparticles *J. Mater. Sci.* **48** 95–107
- [32] Dastjerdi R and Montazer M 2010 A review on the application of inorganic nano-structured materials in the modification of textiles: focus on anti-microbial properties *Colloids Surf. B* **79** 5–18
- [33] Simon-Deckers A, Loo S, Mayne-L’Hermite M, Herlin-Boime N, Menguy N, Reynaud C, Gouget B and Carriere M 2009 Size-, composition- and shape-dependent toxicological impact of metal oxide nanoparticles and carbon nanotubes toward bacteria *Environ. Sci. Technol.* **43** 8423–9
- [34] Nateghi M R and Hajimirzababa H 2014 Effect of silver nanoparticles morphologies on antimicrobial properties of cotton fabrics *J. Text. Inst.* **1–8**
- [35] Tang B, Wang J F, Xu S P, Afrin T, Xu W Q, Sun L and Wang X G 2011 Application of anisotropic silver nanoparticles: multifunctionalization of wool fabric *J. Colloid Interface Sci.* **356** 513–8
- [36] Sivakumar P M, Balaji S, Prabhawathi V, Neelakandan R, Manoharan P T and Doble M 2010 Effective antibacterial adhesive coating on cotton fabric using ZnO nanorods and chalcone *Carbohydr. Polym.* **79** 717–23
- [37] Song Q W, Li Y, Xing J W, Hu J Y and Yuen C W M 2007 Thermal stability of composite phase change material microcapsules incorporated with silver nano-particles *Polymer* **48** 3317–23
- [38] Anita S, Ramachandran T, Rajendran R, Koushik C V and Mahalakshmi M 2011 A study of the antimicrobial property of encapsulated copper oxide nanoparticles on cotton fabric *Text. Res. J.* **81** 1081–8
- [39] Khalil-Abad M S, Yazdanshenas M E and Nateghi M R 2009 Effect of cationization on adsorption of silver nanoparticles on cotton surfaces and its antibacterial activity *Cellulose* **16** 1147–57
- [40] Nischala K, Rao T N and Hebalkar N 2011 Silica–silver core–shell particles for antibacterial textile application *Colloids Surf. B* **82** 203–8
- [41] Klemenčič D, Tomšič B, Kovač F, Žerjav M, Simončič A and Simončič B 2014 Preparation of novel fibre–silica–Ag composites: the influence of fibre structure on sorption capacity and antimicrobial activity *J. Mater. Sci.* **49** 3785–94
- [42] Tarimala S, Kothari N, Abidi N, Hequet E, Fralick J and Dai L L 2006 New approach to antibacterial treatment of cotton fabric with silver nanoparticle-doped silica using sol-gel process *J. Appl. Polym. Sci.* **101** 2938–43
- [43] Lee H Y, Park H K, Lee Y M, Kim K and Park S B 2007 A practical procedure for producing silver nanocoated fabric and its antibacterial evaluation for biomedical applications *Chem. Commun.* **28** 2959–61
- [44] Falletta E, Bonini M, Fratini E, Lo Nostro A, Pesavento G, Becheri A, Lo Nostro P, Canton P and Baglioni P 2008 Clusters of poly(acrylates) and silver nanoparticles: structure and applications for antimicrobial fabrics *J. Phys. Chem. C* **112** 11758–66
- [45] Zhang F, Wu X L, Chen Y Y and Lin H 2009 Application of silver nanoparticles to cotton fabric as an antibacterial textile finish *Fibers Polym.* **10** 496–501

- [46] Montazer M, Alimohammadi F, Shamei A and Rahimi M K 2012 Durable antibacterial and cross-linking cotton with colloidal silver nanoparticles and butane tetracarboxylic acid without yellowing *Colloids Surf. B* **89** 196–202
- [47] Shahid ul I, Shahid M and Mohammad F 2013 Green chemistry approaches to develop antimicrobial textiles based on sustainable biopolymers—a review *Ind. Eng. Chem. Res.* **52** 5245–60
- [48] Hebeish A, El-Naggar M E, Fouda M M G, Ramadan M A, Al-Deyab S S and El-Rafie M H 2011 Highly effective antibacterial textiles containing green synthesized silver nanoparticles *Carbohydr. Polym.* **86** 936–40
- [49] Raghavendra G M, Jayaramudu T, Varaprasad K, Sadiku R, Ray S S and Mohana R K 2013 Cellulose–polymer–Ag nanocomposite fibers for antibacterial fabrics/skin scaffolds *Carbohydr. Polym.* **93** 553–60
- [50] Mahltig B, Tatlis B, Fahmi A and Haase H 2013 Dendrimer stabilized silver particles for the antimicrobial finishing of textiles *J. Text. Inst.* **104** 1042–8
- [51] Abdelgawad A M, Hudson S M and Rojas O J 2014 Antimicrobial wound dressing nanofiber mats from multicomponent (chitosan/silver-NPs/polyvinyl alcohol) systems *Carbohydr. Polym.* **100** 166–78
- [52] Thomas V, Bajpai M and Bajpai S K 2010 *In situ* formation of silver nanoparticles within chitosan-attached cotton fabric for antibacterial property *J. Ind. Text.* **40** 229–45
- [53] Ali S W, Rajendran S and Joshi M 2011 Synthesis and characterization of chitosan and silver loaded chitosan nanoparticles for bioactive polyester *Carbohydr. Polym.* **83** 438–46
- [54] Perelshtein I, Applerot G, Perkas N, Guibert G, Mikhailov S and Gedanken A 2008 Sonochemical coating of silver nanoparticles on textile fabrics (nylon, polyester and cotton) and their antibacterial activity *Nanotechnology* **19** 245705
- [55] Abramov O V, Gedanken A, Koltypin Y, Perkas N, Perelshtein I, Joyce E and Mason T J 2009 Pilot scale sonochemical coating of nanoparticles onto textiles to produce biocidal fabrics *Surf. Coat. Technol.* **204** 718–22
- [56] El-Nahal I M, Zourab S M, Kodeh F S, Semane M, Genois I and Babonneau F 2012 Nano-structured copper oxide-cotton fibers: synthesis, characterization and applications *Int. Nano Lett.* **2** 14
- [57] Chen C Y and Chiang C L 2008 Preparation of cotton fibers with antibacterial silver nanoparticles *Mater. Lett.* **62** 3607–9
- [58] Perera S, Bhushan B, Bandara R, Rajapakse G, Rajapakse S and Bandara C 2013 Morphological, antimicrobial, durability, and physical properties of untreated and treated textiles using silver-nanoparticles *Colloids Surf. A* **436** 975–89
- [59] Sun G and Hong K H 2012 Photo-induced antimicrobial and decontaminating agents: recent progresses in polymer and textile applications *Text. Res. J.* **83** 532–42
- [60] Gorjanc M, Bukosek V, Gorenek M and Mozetic M 2010 CF4 plasma and silver functionalized cotton *Text. Res. J.* **80** 2204–13
- [61] Ilic V, Saponjic Z, Vodnik V, Lazovic S, Dimitrijevic S, Jovancic P, Nedeljkovic J M and Radetic M 2010 Bactericidal efficiency of silver nanoparticles deposited onto radio frequency plasma pretreated polyester fabrics *Ind. Eng. Chem. Res.* **49** 7287–93
- [62] Gorenek M, Gorjanc M, Bukosek V, Kovac J, Jovancic P and Mihailovic D 2009 Functionalization of PET fabrics by corona and nano silver *Text. Res. J.* **80** 253–62
- [63] Radetic M, Ilic V, Vodnik V, Dimitrijevic S, Jovancic P, Saponjic Z and Nedeljkovic J M 2008 Antibacterial effect of silver nanoparticles deposited on corona-treated polyester and polyamide fabrics *Polym. Adv. Technol.* **19** 1816–21
- [64] Ilic V, Saponjic Z, Vodnik V, Molina R, Dimitrijevic S, Jovancic P, Nedeljkovic J and Radetic M 2009 Antifungal efficiency of corona pretreated polyester and polyamide fabrics loaded with Ag nanoparticles *J. Mater. Sci.* **44** 3983–90
- [65] Lu Z, Meng M, Jiang Y and Xie J 2014 UV-assisted *in situ* synthesis of silver nanoparticles on silk fibers for antibacterial applications *Colloids Surf. A* **447** 1–7

- [66] Perkas N, Amirian G, Dubinsky S, Gazit S and Gedanken A 2007 Ultrasound-assisted coating of nylon 6,6 with silver nanoparticles and its antibacterial activity *J. Appl. Polym. Sci.* **104** 1423–30
- [67] Yuranova T, Rincon A G, Bozzi A, Parra S, Pulgarin C, Albers P and Kiwi J 2003 Antibacterial textiles prepared by RF-plasma and vacuum-UV mediated deposition of silver *J. Photochem. Photobiol. A* **161** 27–34
- [68] Bozzi A, Yuranova T and Kiwi J 2005 Self-cleaning of wool-polyamide and polyester textiles by TiO₂-rutile modification under daylight irradiation at ambient temperature *J. Photochem. Photobiol. A* **172** 27–34
- [69] Vu N K, Zille A, Oliveira F R, Carneiro N and Souto A P 2013 Effect of particle size on silver nanoparticle deposition onto dielectric barrier discharge (DBD) plasma functionalized polyamide fabric *Plasma Processes Polym.* **10** 285–96
- [70] Saponjic Z, Ilic V, Vodnik V, Mihailovic D, Jovancic P, Nedeljkovic J and Radetic M 2008 The antifungal activity of corona treated polyamide and polyester fabrics loaded with silver nanoparticles *Publ. Astron. Obs. Belgrade* **84** 411–4
- [71] Wang S H, Hou W S, Wei L Q, Jia H S, Liu X G and Xu B S 2007 Antibacterial activity of nano-SiO₂ antibacterial agent grafted on wool surface *Surf. Coat. Technol.* **202** 460–5
- [72] Yuranova T, Laub D and Kiwi J 2007 Synthesis, activity and characterization of textiles showing self-cleaning activity under daylight irradiation *Catal. Today* **122** 109–17
- [73] Pant H R, Bajgai M P, Nam K T, Seo Y A, Pandeya D R, Hong S T and Kim H Y 2011 Electrospun nylon-6 spider-net like nanofiber mat containing TiO₂ nanoparticles: A multifunctional nanocomposite textile material *J. Hazard. Mater.* **185** 124–30
- [74] Kangwansupamonkon W, Lauruengtana V, Surassmo S and Ruktanonchai U 2009 Antibacterial effect of apatite-coated titanium dioxide for textiles applications *Nanomed. Nanotechnol. Biol. Med.* **5** 240–9
- [75] Kathirvelu S, D'Souza L and Dhurai B 2008 A comparative study of multifunctional finishing of cotton and P/C blended fabrics treated with titanium dioxide/zinc oxide nanoparticles *Indian J. Sci. Technol.* **1** 1–12
- [76] Khurana N and Adivarekar R V 2013 Effect of dispersing agents on synthesis of nano titanium oxide and its application for antimicrobial property *Fibers Polym.* **14** 1094–100
- [77] Sung-Suh H M, Choi J R, Hah H J, Koo S M and Bae Y C 2004 Comparison of Ag deposition effects on the photocatalytic activity of nanoparticulate TiO₂ under visible and UV light irradiation *J. Photochem. Photobiol. A* **163** 37–44
- [78] Dastjerdi R, Mojtahedi M R M, Shoshtari A M and Khosroshahi A 2010 Investigating the production and properties of Ag/TiO₂/PP antibacterial nanocomposite filament yarns *J. Text. Inst.* **101** 204–13
- [79] Son B, Yeom B Y, Song S H, Lee C S and Hwang T S 2009 Antibacterial electrospun chitosan/poly(vinyl alcohol) nanofibers containing silver nitrate and titanium dioxide *J. Appl. Polym. Sci.* **111** 2892–9
- [80] Li G H, Liu H, Zhao H S, Gao Y Q, Wang J Y, Jiang H D and Boughton R I 2011 Chemical assembly of TiO₂ and TiO₂@Ag nanoparticles on silk fiber to produce multifunctional fabrics *J. Colloid Interface Sci.* **358** 307–15
- [81] Montazer M, Behzadnia A, Pakdel E, Rahimi M K and Moghadam M B 2011 Photo induced silver on nano titanium dioxide as an enhanced antimicrobial agent for wool *J. Photochem. Photobiol. B* **103** 207–14
- [82] Wakefield G, Green M, Lipscomb S and Flutter B 2004 Modified titania nanomaterials for sunscreen applications—reducing free radical generation and DNA damage *Mater. Sci. Technol.* **20** 985–8
- [83] Perelshtein I, Applerot G, Perkas N, Wehrschetz-Sigl E, Hasmann A, Guebitz G M and Gedanken A 2009 Antibacterial properties of an *in situ* generated and simultaneously deposited nanocrystalline ZnO on fabrics *ACS Appl. Mater. Interfaces* **1** 363–6
- [84] Vigneshwaran N, Kumar S, Kathe A A, Varadarajan P V and Prasad V 2006 Functional finishing of cotton fabrics using zinc oxide-soluble starch nanocomposites *Nanotechnology* **17** 5087–95
- [85] Uğur Ş S, Sarıışık M, Aktaş A H, Uçar M Ç and Erden E 2010 Modifying of cotton fabric surface with nano-ZnO multilayer films by layer-by-layer deposition method *Nanoscale Res. Lett.* **5** 1204–10

- [86] Erem A D, Ozcan G and Skrifvars M 2011 Antibacterial activity of PA₆/ZnO nanocomposite fibers *Text. Res. J.* **81** 1638–46
- [87] Zhang G, Liu Y, Morikawa H and Chen Y 2013 Application of ZnO nanoparticles to enhance the antimicrobial activity and ultraviolet protective property of bamboo pulp fabric *Cellulose* **20** 1877–84
- [88] Sorna Gowri V, Almeida L, Amorim M T P, Pacheco N C, Souto A P, Esteves M F and Sanghi S K 2010 Functional finishing of polyamide fabrics using ZnO–PMMA nanocomposites *J. Mater. Sci.* **45** 2427–35
- [89] El.Shafei A and Abou-Okeil A 2011 ZnO/carboxymethyl chitosan bionano-composite to impart antibacterial and UV protection for cotton fabric *Carbohydr. Polym.* **83** 920–5
- [90] Li Q L, Mahendra S, Lyon D Y, Brunet L, Liga M V, Li D and Alvarez P J J 2008 Antimicrobial nanomaterials for water disinfection and microbial control: Potential applications and implications *Water Res.* **42** 4591–602
- [91] Perelshtein I, Applerot G, Perkas N, Wehrsuetz-Sigl E, Hasmann A, Guebitz G and Gedanken A 2009 CuO-cotton nanocomposite: formation, morphology, and antibacterial activity *Surf. Coat. Technol.* **204** 54–7
- [92] Rajendran R, Balakumar C, Ahammed H A M, Jayakumar S, Vaideki K and Rajesh E 2010 Use of zinc oxide nano particles for production of antimicrobial textiles *Int. J. Eng. Sci. Technol.* **2** 202–8
- [93] Usha R, Prabu E, Palaniswamy M, Venil C K and Rajendran R 2010 Synthesis of metal oxide nano particles by streptomyces Sp for development of antimicrobial textiles *Glob. J. Biotechnol. Biochem.* **5** 153–60
- [94] Teli M D and Sheikh J 2013 Modified bamboo rayon–copper nanoparticle composites as antibacterial textiles *Int. J. Biol. Macromol.* **61** 302–7
- [95] Perelshtein I *et al* 2013 The sonochemical coating of cotton withstands 65 washing cycles at hospital washing standards and retains its antibacterial properties *Cellulose* **20** 1215–21
- [96] Ren G, Hu D, Cheng E W C, Vargas-Reus M A, Reip P and Allaker R P 2009 Characterisation of copper oxide nanoparticles for antimicrobial applications *Int. J. Antimicrob. Agents* **33** 587–90
- [97] Komeily-Nia Z, Montazer M and Latifi M 2013 Synthesis of nano copper/nylon composite using ascorbic acid and CTAB *Colloids Surf. A* **439** 167–75
- [98] Gouda M 2011 Nano-zirconium oxide and nano-silver oxide/cotton gauze fabrics for antimicrobial and wound healing acceleration *J. Ind. Text.* **41** 222–40
- [99] Tang B, Sun L, Kaur J, Yu Y and Wang X 2014 *In-situ* synthesis of gold nanoparticles for multifunctionalization of silk fabrics *Dyes Pigm.* **103** 183–90
- [100] Harifi T and Montazer M 2014 *In situ* synthesis of iron oxide nanoparticles on polyester fabric utilizing color, magnetic, antibacterial and sono-Fenton catalytic properties *J. Mater. Chem. B* **2** 272
- [101] Damm C, Münstedt H and Rösch A 2008 The antimicrobial efficacy of polyamide 6/silver-nano- and microcomposites *Mater. Chem. Phys.* **108** 61–6
- [102] Jeong S H, Yeo S Y and Yi S C 2005 The effect of filler particle size on the antibacterial properties of compounded polymer/silver fibers *J. Mater. Sci.* **40** 5407–11
- [103] Yeo S Y and Jeong S H 2003 Preparation and characterization of polypropylene/silver nanocomposite fibers *Polym. Int.* **52** 1053–7
- [104] Son W K, Youk J H, Lee T S and Park W H 2004 Preparation of antimicrobial ultrafine cellulose acetate fibers with silver nanoparticles *Macromol. Rapid Commun.* **25** 1632–7
- [105] Dong H, Wang D, Sun G and Hinestroza J P 2008 Assembly of metal nanoparticles on electrospun nylon 6 nanofibers by control of interfacial hydrogen-bonding interactions *Chem. Mater.* **20** 6627–32
- [106] Duan Y-Y, Jia J, Wang S-H, Yan W, Jin L and Wang Z-Y 2007 Preparation of antimicrobial poly(ϵ -caprolactone) electrospun nanofibers containing silver-loaded zirconium phosphate nanoparticles *J. Appl. Polym. Sci.* **106** 1208–14
- [107] An J, Zhang H, Zhang J T, Zhao Y H and Yuan X Y 2009 Preparation and antibacterial activity of electrospun chitosan/poly(ethylene oxide) membranes containing silver nanoparticles *Colloid Polym. Sci.* **287** 1425–34

- [108] Xu X Y, Yang Q B, Wang Y Z, Yu H J, Chen X S and Jing X B 2006 Biodegradable electrospun poly(L-lactide) fibers containing antibacterial silver nanoparticles *Eur. Polym. J.* **42** 2081–7
- [109] Li L, Li Y, Li J S, Yao L, Mak A F T, Ko F and Qin L 2009 Antibacterial properties of nanosilver PLLA fibrous membranes *J. Nanomater.* **9** 168041
- [110] Hong K H, Park J L, Sul I H, Youk J H and Kang T J 2006 Preparation of antimicrobial poly(vinyl alcohol) nanofibers containing silver nanoparticles *J. Polym. Sci. B* **44** 2468–74
- [111] Hang A T, Tae B and Park J S 2010 Non-woven mats of poly(vinyl alcohol)/chitosan blends containing silver nanoparticles: fabrication and characterization *Carbohydr. Polym.* **82** 472–9
- [112] Li W L, Wang J J and Dai L X 2011 Preparation and antibacterial activity of poly (vinyl alcohol)/silk fibroin composite nanofibers containing silver nanoparticles *Adv. Mater. Res.* **175–176** 105–9
- [113] Konwarh R, Karak N and Misra M 2013 Electrospun cellulose acetate nanofibers: The present status and gamut of biotechnological applications *Biotechnol. Adv.* **31** 421–37
- [114] Liu X, Lin T, Gao Y, Xu Z, Huang C, Yao G, Jiang L, Tang Y and Wang X 2012 Antimicrobial electrospun nanofibers of cellulose acetate and polyester urethane composite for wound dressing *J. Biomed. Mater. Res. B* **100** 1556–65
- [115] Fang J, Niu H, Lin T and Wang X 2008 Applications of electrospun nanofibers *Chin. Sci. Bull.* **53** 2265–86
- [116] Shi Q, Vitchuli N, Nowak J, Caldwell J M, Breidt F, Bourham M, Zhang X and McCord M 2011 Durable antibacterial Ag/polyacrylonitrile (Ag/PAN) hybrid nanofibers prepared by atmospheric plasma treatment and electrospinning *Eur. Polym. J.* **47** 1402–9
- [117] Zhang H T, Li S B, White C J B, Ning X, Nie H L and Zhu L M 2009 Studies on electrospun nylon-6/chitosan complex nanofiber interactions *Electrochim. Acta* **54** 5739–45
- [118] Santos C, Silva C J, Büttel Z, Guimarães R, Pereira S B, Tamagnini P and Zille A 2014 Preparation and characterization of polysaccharides/PVA blend nanofibrous membranes by electrospinning method *Carbohydr. Polym.* **99** 584–92
- [119] Schiffman J D and Schauer C L 2008 A review: electrospinning of biopolymer nanofibers and their applications *Polym. Rev.* **48** 317–52
- [120] Teo W-E and Ramakrishna S 2009 Electrospun nanofibers as a platform for multifunctional, hierarchically organized nanocomposite *Compos. Sci. Technol.* **69** 1804–17
- [121] Chen M-C, Mi F-L, Liao Z-X, Hsiao C-W, Sonaje K, Chung M-F, Hsu L-W and Sung H-W 2013 Recent advances in chitosan-based nanoparticles for oral delivery of macromolecules *Adv. Drug Delivery. Rev.* **65** 865–79
- [122] Kim S S and Lee J 2014 Antibacterial activity of polyacrylonitrile–chitosan electrospun nanofibers *Carbohydr. Polym.* **102** 231–7
- [123] Perelshtein I *et al* 2013 Chitosan and chitosan–ZnO-based complex nanoparticles: formation, characterization, and antibacterial activity *J. Mater. Chem. B* **1** 1968–76
- [124] Vellingiri K, Ramachandran T and Senthilkumar M 2013 Eco-friendly application of nano chitosan in antimicrobial coatings in the textile industry *Nanosci. Nanotechnol. Lett.* **5** 519–29
- [125] Hebeish A, Sharaf S and Farouk A 2013 Utilization of chitosan nanoparticles as a green finish in multifunctionalization of cotton textile *Int. J. Biol. Macromol.* **60** 10–7
- [126] Kong M, Chen X G, Xing K and Park H J 2010 Antimicrobial properties of chitosan and mode of action: a state of the art review *Int. J. Food Microbiol.* **144** 51–63
- [127] El-Sheikh M A, El Gabry L K and Ibrahim H M 2013 Photosynthesis of carboxymethyl starch-stabilized silver nanoparticles and utilization to impart antibacterial finishing for wool and acrylic fabrics *J. Polym.* **2013** 1–9
- [128] Teli M D and Sheikh J 2013 Study of grafted silver nanoparticle containing durable antibacterial bamboo rayon *Cellul. Chem. Technol.* **47** 69–75
- [129] Son W K, Youk J H and Park W H 2006 Antimicrobial cellulose acetate nanofibers containing silver nanoparticles *Carbohydr. Polym.* **65** 430–4

- [130] Kim H W, Kim B R and Rhee Y H 2010 Imparting durable antimicrobial properties to cotton fabrics using alginate-quaternary ammonium complex nanoparticles *Carbohydr. Polym.* **79** 1057–62
- [131] Duran N, Marcato P D, De Souza G I H, Alves O L and Esposito E 2007 Antibacterial effect of silver nanoparticles produced by fungal process on textile fabrics and their effluent treatment *J. Biomed. Nanotechnol.* **3** 203–8
- [132] Lee H J, Yeo S Y and Jeong S H 2003 Antibacterial effect of nanosized silver colloidal solution on textile fabrics *J. Mater. Sci.* **38** 2199–204
- [133] Su W, Wei S S, Hu S Q and Tang J X 2011 Antimicrobial finishing of cotton textile with nanosized silver colloids synthesized using polyethylene glycol *J. Text. Inst.* **102** 150–6
- [134] Ngo V K T and Nguyen T P P 2009 Investigation of antibacterial activity of cotton fabric incorporating nano silver colloid *Apctp-Asean Workshop on Advanced Materials Science and Nanotechnology (Amsn08) J. Phys.: Conf. Ser.* **187** 012072
- [135] Marcato P D, Nakasato G, Brocchi M, Melo P S, Huber S C, Ferreira I R, Alves O L and Durán N 2012 Biogenic silver nanoparticles: antibacterial and cytotoxicity applied to textile fabrics *J. Nano Res.* **20** 69–76
- [136] Ilic V, Saponjic Z, Vodnik V, Potkonjak B, Jovancic P, Nedeljkovic J and Radetic M 2009 The influence of silver content on antimicrobial activity and color of cotton fabrics functionalized with Ag nanoparticles *Carbohydr. Polym.* **78** 564–9
- [137] Velmurugan P, Cho M, Lee S-M, Park J-H, Bae S and Oh B-T 2014 Antimicrobial fabrication of cotton fabric and leather using green-synthesized nanosilver *Carbohydr. Polym.* **106** 319–25
- [138] Zhang D, Chen L, Zang C, Chen Y and Lin H 2013 Antibacterial cotton fabric grafted with silver nanoparticles and its excellent laundering durability *Carbohydr. Polym.* **92** 2088–94
- [139] Vankar P S and Shukla D 2011 Biosynthesis of silver nanoparticles using lemon leaves extract and its application for antimicrobial finish on fabric *Appl. Nanosci.* **2** 163–8
- [140] Budama L, Çakır B A, Topel Ö and Hoda N 2013 A new strategy for producing antibacterial textile surfaces using silver nanoparticles *Chem. Eng. J.* **228** 489–95
- [141] Ravindra S, Mohan Y M, Reddy N N and Raju K M 2010 Fabrication of antibacterial cotton fibres loaded with silver nanoparticles via 'Green Approach' *Colloids Surfaces A* **367** 31–40
- [142] Shinde V V, Jadhav P R, Kim J H and Patil P S 2013 One-step synthesis and characterization of anisotropic silver nanoparticles: application for enhanced antibacterial activity of natural fabric *J. Mater. Sci.* **48** 8393–401
- [143] Paladini F, De Simone S, Sannino A and Pollini M 2014 Antibacterial and antifungal dressings obtained by photochemical deposition of silver nanoparticles *J. Appl. Polym. Sci.* **131** 40326
- [144] Sataev M S, Koshkarbaeva S T, Tleuova A B, Perni S, Aidarova S B and Prokopovich P 2014 Novel process for coating textile materials with silver to prepare antimicrobial fabrics *Colloids Surf. A* **442** 146–51
- [145] Saengkiattiyut K, Rattanawaleedirojn P and Sangsuk S 2008 A study on antimicrobial efficacy of nano silver containing textile *Chiang Mai University J. Nat. Sci.* **7** 33–6
- [146] Kulthong K, Srisung S, Boonpavanitchakul K, Kangwansupamonkon W and Maniratanachote R 2010 Determination of silver nanoparticle release from antibacterial fabrics into artificial sweat *Part. Fibre Toxicol.* **7** 1–9
- [147] Xue C-H, Chen J, Yin W, Jia S-T and Ma J-Z 2012 Superhydrophobic conductive textiles with antibacterial property by coating fibers with silver nanoparticles *Appl. Surf. Sci.* **258** 2468–72
- [148] Abdel-Mohsen A M, Abdel-Rahman R M, Hrdina R, Imramovský A, Burgert L and Aly A S 2012 Antibacterial cotton fabrics treated with core-shell nanoparticles *Int. J. Biol. Macromol.* **50** 1245–53
- [149] Arain R A, Khatri Z, Memon M H and Kim I-S 2013 Antibacterial property and characterization of cotton fabric treated with chitosan/AgCl-TiO₂ colloid *Carbohydr. Polym.* **96** 326–31
- [150] Rajendran R, Radhai R, Kotresh T M and Csiszar E 2013 Development of antimicrobial cotton fabrics using herb loaded nanoparticles *Carbohydr. Polym.* **91** 613–7

- [151] Gupta N, Khurana N and Adivarekar R 2013 Synthesis and application of nano copper oxide for antimicrobial property *Int. J. Eng.* **2** 2583–2595
- [152] Abramova A, Gedanken A, Popov V, Ooi E-H, Mason T J, Joyce E M, Beddow J, Perelshtein I and Bayazitov V 2013 A sonochemical technology for coating of textiles with antibacterial nanoparticles and equipment for its implementation *Mater. Lett.* **96** 121–4
- [153] Sundaresan K, Sivakumar A, Vigneswaran C and Ramachandran T 2011 Influence of nano titanium dioxide finish, prepared by sol-gel technique, on the ultraviolet protection, antimicrobial, and self-cleaning characteristics of cotton fabrics *J. Ind. Text.* **41** 259–77
- [154] Perelshtein I, Apperlot G, Perkash N, Grinblat J and Gedanken A 2012 A one-step process for the antimicrobial finishing of textiles with crystalline TiO₂ nanoparticles *Chem. Eur. J.* **18** 4575–82
- [155] Zarei L, Shahidi S, Elahi S M and Boochani A 2013 *In situ* growth of zinc oxide nanoparticles on cotton fabric using sonochemical method *Adv. Mater. Res.* **856** 53–9
- [156] Çakır B A, Budama L, Topel Ö and Hoda N 2012 Synthesis of ZnO nanoparticles using PS-b-PAA reverse micelle cores for UV protective, self-cleaning and antibacterial textile applications *Colloids Surf. A* **414** 132–9
- [157] Perelshtein I *et al* 2012 Enzymatic pre-treatment as a means of enhancing the antibacterial activity and stability of ZnO nanoparticles sonochemically coated on cotton fabrics *J. Mater. Chem.* **22** 10736–42
- [158] Farouk A, Moussa S, Ulbricht M, Schollmeyer E and Textor T 2013 ZnO-modified hybrid polymers as an antibacterial finish for textiles *Text. Res. J.* **84** 40–51
- [159] Selvam S and Sundrarajan M 2012 Functionalization of cotton fabric with PVP/ZnO nanoparticles for improved reactive dyeability and antibacterial activity *Carbohydr. Polym.* **87** 1419–24
- [160] Subash A A, Chandramouli K V, Ramachandran T, Rajendran R and Muthusamy M 2011 Preparation, characterization, and functional analysis of zinc oxide nanoparticle-coated cotton fabric for antibacterial efficacy *J. Text. Inst.* **1–6**
- [161] Petkova P, Francesko A, Fernandes M M, Mendoza E, Perelshtein I, Gedanken A and Tzanov T 2014 Sonochemical coating of textiles with hybrid ZnO/chitosan antimicrobial nanoparticles *ACS Appl. Mater. Interfaces* **6** 1164–72
- [162] Farouk A, Moussa S, Ulbricht M and Textor T 2012 ZnO nanoparticles-chitosan composite as antibacterial finish for textiles *Int. J. Carbohydr. Chem.* **2012** 1–8
- [163] Rattanawaleedirojn P, Saengkiattiyut K and Sangsuk S 2008 Antibacterial efficacy of nano silver finished fabric on staphylococcus aureus and preliminary test on its safety *Chiang Mai University J. Nat. Sci.* **7** 75–9
- [164] Ilic V, Saponjic Z, Vodnik V, Mihailovic D, Jovancic P, Nedeljkovic J and Radetic M 2009 The study of coloration and antibacterial efficiency of corona activated dyed polyamide and polyester fabrics loaded with Ag nanoparticles *Fibers Polym.* **10** 650–6
- [165] Sedaghat S and Nasser A 2011 Synthesis and stabilization of Ag nanoparticles on a polyamide (nylon 6,6) surface and its antibacterial effects *Int. Nano Lett.* **1** 22–4
- [166] Gorensek M and Recelj P 2009 Reactive dyes and nano-silver on PA6 micro knitted goods *Text. Res. J.* **79** 138–46
- [167] Dubas S T, Kumlangdudsana P and Potiyaraj P 2006 Layer-by-layer deposition of antimicrobial silver nanoparticles on textile fibers *Colloids Surf. A* **289** 105–9
- [168] Kumar V, Jolival C, Pulpytel J, Jafari R and Arefi-Khonsari F 2013 Development of silver nanoparticle loaded antibacterial polymer mesh using plasma polymerization process *J. Biomed. Mater. Res. A* **101A** 1121–32
- [169] Dastjerdi R, Montazer M and Shahsavan S 2009 A new method to stabilize nanoparticles on textile surfaces *Colloids Surf. A* **345** 202–10
- [170] Brzezinski S, Malinowska G, Kowalczyk D, Kaleta A, Borak B, Jasierski M, Dabek K, Baszczuk A and Tracz A 2012 Antibacterial and fungicidal coating of textile-polymeric materials filled with bioactive nano- and submicro-particles *Fibres Text. East. Eur.* **20** 70–7

- [171] Mihailovic D, Saponjic Z, Radoicic M, Radetic T, Jovancic P, Nedeljkovic J and Radetic M 2010 Functionalization of polyester fabrics with alginates and TiO₂ nanoparticles *Carbohydr. Polym.* **79** 526–32
- [172] Fouda M M G, El-Aassar M R and Al-Deyab S S 2013 Antimicrobial activity of carboxymethyl chitosan/polyethylene oxide nanofibers embedded silver nanoparticles *Carbohydr. Polym.* **92** 1012–7
- [173] Jeong S H, Hwang Y H and Yi S C 2005 Antibacterial properties of padded PP/PE nonwovens incorporating nano-sized silver colloids *J. Mater. Sci.* **40** 5413–8
- [174] Zhang D S, Toh G W, Lin H and Chen Y Y 2012 *In situ* synthesis of silver nanoparticles on silk fabric with PNP for antibacterial finishing *J. Mater. Sci.* **47** 5721–8
- [175] Sashina E S, Dubkova O I, Novoselov N P, Goralsky J J, Szykowska M I, Lesniewska E, Maniukiewicz W and Strobin G 2009 Silver nanoparticles on fibers and films of Bombyx mori silk fibroin *Russ. J. Appl. Chem.* **82** 974–80
- [176] Gulrajani M L, Gupta D, Periyasamy S and Muthu S G 2008 Preparation and application of silver nanoparticles on silk for imparting antimicrobial properties *J. Appl. Polym. Sci.* **108** 614–23
- [177] Moazami A, Montazer M, Rashidi A and Rahimi M K 2010 Antibacterial properties of raw and degummed silk with nanosilver in various conditions *J. Appl. Polym. Sci.* **118** 253–8
- [178] Dickerson M B, Knight C L, Gupta M K, Luckarift H R, Drummy L F, Jespersen M L, Johnson G R and Naik R R 2011 Hybrid fibers containing protein-templated nanomaterials and biologically active components as antibacterial materials *Mater. Sci. Eng. C* **31** 1748–58
- [179] Chang S Q, Kang B, Dai Y D and Chen D 2009 Synthesis of antimicrobial silver nanoparticles on silk fibers via gamma-radiation *J. Appl. Polym. Sci.* **112** 2511–5
- [180] Miao H C, Lin H and Chen C Y 2010 Preparation of cactus nanoparticles and their application in antibacterial treatment of B.mori silk *J. Textile Res.* **31** 88–91
- [181] Liu Y, Zhang F, Lin H and Chen Y Y 2009 Nano-silver as an antibacterial finish used to silk fabric by the steam method *Proc. of the Fiber Society 2009 Spring Conf.* vols I and II pp 1408–10
- [182] Tang B, Li J, Hou X, Afrin T, Sun L and Wang X 2013 Colorful and antibacterial silk fiber from anisotropic silver nanoparticles *Ind. Eng. Chem. Res.* **52** 4556–63
- [183] Lu Y H, Chen Y Y, Lin H, Wang C and Yang Z D 2010 Preparation of chitosan nanoparticles and their application to antheraea pernyi silk *J. Appl. Polym. Sci.* **117** 3362–9
- [184] El-Molla M M, El-Khatib E M, El-Gammal M S and Abdel-Fattah S H 2011 Nanotechnology to improve coloration and antimicrobial properties of silk fabrics *Indian J. Fibre Textile Res.* **36** 266–71
- [185] Mahltig B, Fiedler D and Simon P 2011 Silver-containing sol–gel coatings on textiles: antimicrobial effect as a function of curing treatment *J. Text. Inst.* **102** 739–45
- [186] Ki H Y, Kim J H, Kwon S C and Jeong S H 2007 A study on multifunctional wool textiles treated with nano-sized silver *J. Mater. Sci.* **42** 8020–4
- [187] Tang B, Wang J F, Xu S P, Afrin T, Tao J L, Xu W Q, Sun L and Wang X G 2012 Function improvement of wool fabric based on surface assembly of silica and silver nanoparticles *Chem. Eng. J.* **185** 366–73
- [188] Montazer M and Seifollahzadeh S 2011 Enhanced self-cleaning, antibacterial and UV protection properties of nano TiO₂ treated textile through enzymatic pretreatment *Photochem. Photobiol.* **87** 877–83