

Development of alginate-based hydrogels/cryogels by gelation under pressure

Alexandre Barros^{1,2}, Sakeena Quraishi³, Marta Martins^{1,2}, Raman S.P.³, Pavel Gurikov³,
Irina Smirnova³, Ana Rita C. Duarte^{1,2}, Rui L. Reis^{1,2}

¹ 3B's Research Group – Biomaterials, Biodegradables and Biomimetics, University of Minho, Headquarters of the European Institute of Excellence on Tissue Engineering and Regenerative Medicine, AvePark, 4806-909 Taipas, Guimarães, Portugal

² ICVS/3B's – PT Government Associate Laboratory, Braga/Guimarães, Portugal

³ Hamburg University of Technology, Institute of Thermal Separation Processes, Eißendorfer Straße 38, 21073 Hamburg, Germany

Introduction

A tissue-engineered polymeric scaffold should provide suitable macroporous structure similar to that of extracellular matrix which can induce cellular activities and guide tissue regeneration. Hydrogels are biocompatible hydrophilic polymer structures that can imbibe large amounts of water or biological fluids. Hydrogels are one of the upcoming classes of polymer-based systems that embrace numerous biomedical applications. This work is aimed to present a novel method to fabricate alginate-based calcium crosslinked hydrogels by manipulating gelation at high pressure. The cryogels can be obtained after freeze-drying. Cryogels for biomedical applications are of special interest due to large and highly interconnected pores that provide non-constrained mass transfer for cell growth and proliferation. However, to achieve desirable mechanical properties as well as high adsorption capacity, bimodal meso and macroporous materials are greatly desirable.

Materials and Methods

In this work two freezing regimes were studied in order to convert alginate-based hydrogels into cryogels, namely slow freezing at -80°C and rapid freezing in liquid nitrogen. Finally frozen materials were freeze dried. Hybrid cryogels (1.5 wt% alginate/1.5 wt% biopolymer) with gelatin (Glt), gellan gum (GG), carboxymethylcellulose (CMC) and lignin (Lig) were prepared. Textural properties of the scaffolds were analyzed by SEM and micro-computed tomography. The mechanical properties of the cryogels were characterized in compression mode. Finally, cytotoxicity studies were performed with a L929 cell line.

Results

The results of SEM images indicate that slow freezing (-80°C) lead to purely macroporous materials, whereas rapid freezing in liquid nitrogen resulted in both meso and macroporous structures (Fig. 1). For instance, in case of alginate/GG the

mean pore size of hybrid cryogels was approximately $190\ \mu\text{m}$ with porosity of 52 %.




Fig 1. SEM images of alginate/GG cryogels obtained after rapid and slow freezing followed by freeze-drying.

The mechanical properties of the cryogels were also characterized in compression mode. Results show that the cryogels have Young's modulus values approx. 1 MPa. Cytotoxicity studies were also carried and none of cryogels prepared present any cytotoxicity.

Discussion and Conclusions

Hybrid alginate cryogels blended with gelatin, gellan gum, carboxymethylcellulose and lignin were successfully prepared by gelation under pressure. Rapid freezing with subsequent freeze-drying leads to high porosity both in meso and macro range. The results obtained suggest that developed cryogels have, hereafter, the potential to be used for tissue engineering and regenerative medicine.

References

1. Floren et al. *Biomacromolecules*, **2012**, *13*, 2060.
2. Alnaief et al., *Carbohydr. Polym.*, **2011**, *84*, 1011.
3. García-González et al. *J. Supercrit. Fluids*, **2012**, *66*, 297.

Acknowledgments

Alexandre Barros is grateful for financial support of FCT through grant EXP/QEQ-EPS/0745/2012, SWIMS. The authors acknowledge the funding received from the FCT-DAAD bilateral agreement.