

## Synthetic Protein Biotechnology approaches for the creation of antimicrobial biopolymers

André da Costa<sup>1</sup>, Raul Machado<sup>1</sup>, Artur Ribeiro<sup>1</sup>, Tony Collins<sup>1</sup>, Viruthachalam Thiagarajan<sup>2,3</sup>, Maria Teresa Neves-Petersen<sup>3,4</sup>, José Carlos Rodríguez-Cabello<sup>5,6</sup>, Andreia C. Gomes<sup>1</sup>, and Margarida Casal<sup>1</sup>

<sup>1</sup>CBMA (Centre of Molecular and Environmental Biology), Department of Biology, University of Minho, Campus de Gualtar, 4710-057 Braga, Portugal

<sup>2</sup>School of Chemistry, Bharathidasan University, Tiruchirappalli – 620 024, India

<sup>3</sup>BioPhotonics Group, Nanomedicine Department, International Iberian Nanotechnology Laboratory (INL), P-4715-310 Braga, Portugal

<sup>4</sup>Faculty of Medicine, Aalborg University, DK-9220 Aalborg, Denmark

<sup>5</sup>Bioforge (Group for Advanced Materials and Nanobiotechnology), Centro I+D, Universidad de Valladolid, Valladolid, Spain

<sup>6</sup>Networking Research Centre on Bioengineering, Biomaterials and Nanomedicine (CIBER-BBN), E-47011 Valladolid, Spain

The spread of antimicrobials resistant microorganisms has triggered the search for new ways to treat infections. In the present work we explored the ABP-CM4 peptide properties from *Bombyx mori* for the creation of biopolymers with broad antimicrobial activity. An antimicrobial recombinant protein-based polymer (rPBP) was designed by cloning the DNA sequence coding for ABP-CM4 in frame with the N-terminus of the elastin-like recombinamer consisting of 200 repetitions of the pentamer VPAVG, here named A200. The new rPBP, named CM4-A200, was purified via a simplified nonchromatographic method, making use of the thermoresponsive behavior of the A200 polymer. ABP-CM4 peptide was also purified through the incorporation of a formic acid cleavage site between the peptide and the A200 sequence. In soluble state the antimicrobial activity of both CM4-A200 polymer and ABP-CM4 peptide was poorly effective. However, when the CM4-A200 polymer was processed into free-standing films high antimicrobial activity against Gram-positive and Gram-negative bacteria, yeasts and filamentous fungi was observed. The antimicrobial activity of CM4-A200 was dependent on the physical contact of cells with the film surface. Furthermore, CM4-A200 films did not reveal a cytotoxic effect against both normal human skin fibroblasts and human keratinocytes. Finally, we have developed an optimized ex vivo assay with pig skin demonstrating the antimicrobial properties of the CM4-A200 cast films for skin applications.

### Acknowledgments

This work was supported by FEDER through POFC – COMPETE by FCT through the project PEst-OE/BIA/UI4050/2014. By the Spanish Minister of Economy and Competitiveness (MAT2012-38043-C02-01) and Junta de Castilla y León-JCyL (VA152A12-2 and VA155A12-2), Spain. AC and RM, acknowledge FCT for SFRH/BD/75882/2011 and SFRH-BPD/86470/2012 grants, respectively.