



¹Depto de Bioquímica e Biologia Molecular, UFC (CE-Br),
²Curso de Farmácia, UNIFOR (CE-Br).
email: miguelcerqueira_ebio@hotmail.com

Edible films and coatings play an important role in the quality, transportation, storage and display of a wide range of fresh and processed foods. Polysaccharide coatings have an oil-free appearance, a low caloric content and can be used to increase the shelf life of fresh fruits, since they allow the modification of the internal gas composition of fruits, thus retarding its senescence. The objective of this work was to study the ability of seed galactomannans, with different man:gal relation, from different species of *Leguminosae*: (*Caesalpinha pulcherrima* (2.8:1) and *Adenanthera pavonina* (2:1) as coatings to extend the shelf life of acerola (*Malpighia emarginata*), cajú (*Spondias lutea*), mango (*Mangifera indica*), pitanga (*Eugenia uniflora*) and sirigüela (*Spondias purpurea*) fruits. The surface properties of fresh fruits, the galactomannans relative viscosity as well as the wetting capacity of the coatings were determined. The fruits critical surface tensions were determined by the Zisman method. The critical surface tension for acerola, cajú, mango, pitanga and sirigüela were: 9.39 mN/m, 23.92 mN/m, 22.72 mN/m, 13.42 mN/m, 19.62 mN/m, respectively. The galactomannans were obtained after a heat treatment with boiling ethanol (20 min), followed by manually extraction of the endosperm and solubilization of the gum with water. The soluble material were then precipitated with two volumes of ethanol, and passed through nylon net. When the galactomannans safe grade characteristics were determined, by oral administration to Wistar adult rats, no toxic effects were detected. The galactomannans were then mixed with glycerol (plasticizer), at different gum:glycerol proportions and tested as coatings. The wettability of a solid by a liquid is determined by the spreading coefficient (W_s), that is the balance between adhesion (causes the liquid to spread over the solid) and cohesion (causes the liquid to shrink) forces. It was determined using the sessile-drop method. The wettability was calculated with different mixtures of the gums and a plasticizer (glycerol), and the best concentrations for *C. pulcherrima* and *A. pavonina* gum:glycerol were to acerola: 0.5%:2% and 0.5%:1%; cajú: 0.5%:1% and 0.5%:1%; mango: 1.5%:2% and 1.5%:1%; pitanga: 0.5%:1% and 1.5%:1; sirigüela: 0.5%:1% and 0.5%:1.5%.

Key words: galactomannan, edible films, edible coatings

Supported by: Alfa-Valnatura, CNPq, CAPES, FUNCAP, UMinho, UFC

FP55 Plant Seed Galactomannans as Edible Coatings
Cerqueira, M.A.¹, Lima, A.M.P.², Miranda, M.R.A.², Monteiro-
Moreira, A.C.O.², Moreira, H. H. T.², Vicente, A.A.¹,
Teixeira, J.A.¹ and Moreira, R.A.¹

¹Depto. de Engenharia Biológica, Universidade do Minho,
Braga, Pt.,